

**RUST-OLEUM**<sup>®</sup>  
INDUSTRIAL



## 1085 COLD GALVANISING

# Fast drying zinc rich paint

- Offers long-lasting cathodic protection of metal
- 90% zinc content
- Touch dry in just 15 minutes
- Heat resistance up to 300°C
- Ideal for touching-up galvanised steel, welding seems etc.

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# 1085 COLD GALVANISING

## POPIS PRODUKTU (DLOUHÝ)

Fast drying, zinc rich primer based on an epoxy ester resin. Contains pure zinc as pigment and provides cathodic protection to metal.

## DOPORUČENÉ POUŽITÍ

1085 Cold Galvanizing should be used on new, bare steel, blasted steel or galvanized steel surfaces. 1085 is primarily intended for brush application on small areas or for touch-up. Can be recoated with non-saponifiable coatings. 1085 should be used as a primer or as a single coat in light industrial exposures, corrosive environments and high humidity areas. Zinc content: 90% by weight in the dry film.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	2,76
Úroveň lesku:	Matt
Třída koroze:	C4 vysoká ochrana
Obsah pevných látek v hmotnosti:	90%
Obsah pevných látek v objemu:	47,6%
Tepelná odolnost:	300°C (dry heat)

## DRY TIMES BY 20

Dotykem suché:	15 minutes
Suché na manipulaci:	2 hours
Suchý nátěr:	4 hours
Plně vytvrzené:	3 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

75 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 µm

## TEORETICKÁ SPOTŘEBA

13 m<sup>2</sup>/l = 4,7 m<sup>2</sup>/kg

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. For optimum results remove rust, rust scale, mill scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 50 µm. The surface must be clean and dry during application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use. To avoid settlement of the zinc pigments on the bottom of the can stir regularly during application.

## PODMÍNKY POUŽITÍ

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Up to 5% volume RUST-OLEUM Thinner 160.  
Use natural bristles, long hair brushes.

## APLIKACE A ŘEDĚNÍ: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can at least 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Use RUST-OLEUM Thinner 160 or aromatic hydrocarbons.

## POZNÁMKY

Maximum dry film thickness per coat: 75 µm dry, equals 160 µm wet.  
1085 should preferably be applied in a maximum dry film thickness of 35 µm if recoated.  
On abrasive blasted steels, dry film thickness must of 50µm minimum according to the basting profile, so it fully covers peaks of rugosity.

## DATA SAFETY DATA

Úroveň těkavých organických látek:	440 g/l
VOC readymix:	461 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	600 g/l (2007) / 500 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu