

RUST-OLEUM®
INDUSTRIAL



3333 SUPER ADHESIVE PRIMER

Excellent adhesion on smooth & dense substrates

- Perfect chemical bond without blasting or etching
- Low material usage - A real cost saver
- Can be recoated with virtually any other 2K paint
- Water-based; low odour
- Excellent flow

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3333 SUPER ADHESIVE PRIMER

BESKRIVNING

Water-based epoxy primer for use on smooth floors, like power-floated concrete and tiles.

REKOMMENDERAD ANVÄNDNING

Super Adhesive 3333 should be used on non-porous, dense mineral substrates like tiles or power floated concrete; non-ferrous metals like stainless steel, aluminium or new hot-dip galvanized steel and thermosetting plastics like fibreglass-reinforced polyester or epoxy. Resists light to moderate abrasion, intermittent high humidity and moisture, regular chemical cleaning and spillage of chemicals if recoated with the appropriate RUST-OLEUM System; can be recoated with practically all RUST-OLEUM Epoxy, Polyurethane, Chlorinated Rubber/Vinyl and Acrylic coatings. Classified Class 1 Surface Spread of Flame according BS 476; part 7: 1987.

TEKNISK DATA

Densitet:	1,58
Glansnivå:	Satin
Torrsubstansvolym:	61,9%
Värmebeständighet:	150°C (dry heat)
Blandningsförhållande:	Base : Activator = 0.72 : 0.28 (Volume)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	6 hours
Hanteringstorr:	8 hours
Övermålningsbar:	16 hours (20°C), 24 hours (10°C), 12 hours (30°C) but within 72 hours
Fullt härdad:	8 days
Brukstid:	2 hours

REKOMMENDERAD VÅTFILMSTJOCKLEK

25 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

15 µm

TEORETISK FÖRBRUKNING

41 m²/l

PRAKTISK FÖRBRUKNING

25-30 m²/l. Apply in a very thin layer not more than 25 µm wet (15 µm dry).

YTFÖRBEREDELSE

Remove grease, oil and all other surface contaminations with RUST-OLEUM ND14 or by alkaline or high pressure (steam) cleaning. New concrete should cure and dry for at least 30 days prior to the application of the coatings. The surface must be clean and may be slightly damp during application.

BRUKSANVISNING

Stir individual components thoroughly before mixing them together. Use the boxing method or a low speed mixer.

APPLICERINGSFÖRHÅLLANDEN

Temperature of air and substrate between 10 and 35°C and relative humidity below 70%. The substrate temperature must be at least 5°C above dew point.

APPLICERING OCH SPÄDNING: PENSEL

Always dilute with 20% volume with water. Use brushes based on a mixture of synthetic/natural bristles.

Check wet film thickness, avoid excessive film thickness. Preferably use disposable brushes.

APPLICERING OCH SPÄDNING: ROLLER

Always dilute with 20% volume with water. Use HD foam roller. Check wet film thickness, avoid excessive film thickness. Preferably use disposable rollers.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Up to 20% volume with water. Spray: Gravity cup and pressure cup. Tip size: 1.2 -2.0 mm. Atomizing pressure: 2 - 4 bar. Check wet film thickness, avoid excessive film thickness.

RENGÖRING AV UTRUSTNING/SPILL

Immediately after application with (hot) water and soap.

ANMÄRKNINGAR

Do not try to apply a hiding coat to avoid adhesion issues and water sensitivity. If the relative humidity is high during drying, curing might be retarded.

SÄKERHETSDATA

VOC-nivå:	8 g/l
VOC färdigmix:	8 g/l
VOC-kategori:	A/h
VOC-gräns:	30 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C. **Keep from freezing.**

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu