

RUST-OLEUM®
INDUSTRIAL



5130 DAMP SURFACE PRIMER

Primer for damp floors

- Creates a barrier to stop rising moisture and vapour pressure
- Prevents blistering
- For use on asphalt and concrete
- Very low solvent content
- High build system



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5130 DAMP SURFACE PRIMER

OPIS

Epoxy primer for damp surfaces prevents air/moisture blistering on concrete and asphalt.

ZALECANE UŻYCIE

Suppression of vapor pressure effects to prevent air/moisture blistering on suspect concrete and asphalt balcony surfaces, suspended decking etc.

DANE TECHNICZNE

Gęstość:	1,1
Stopień połysku:	Połysk
Zawartość substancji stałych objętościowo:	96%
Proporcja mieszania:	Base : Activator = 1,7 : 0,8 (Volume)

CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk:	6 hours
Do użytku:	16 hours
Do przemalowania:	After 16 hours, but within 48 hours
Pełne utwardzenie:	2 days
Czas przydatności do użycia:	30 minutes

ZALECANA GRUBOŚĆ WARSTWY NA MOKRO

250 µm

ZALECANA GRUBOŚĆ WARSTWY NA SUCHO

240 µm

ZUŻYCIE TEORETYCZNE

4m²/l

ZUŻYCIE PRAKTYCZNE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRZYGOTOWANIE POWIERZCHNI

Ensure surfaces are sound, clean, contaminant-free and as dry as possible before coating. Thoroughly scrub down all dirty surfaces with Rust-Oleum ND 14 (see PDS) alkaline detergent solution followed by thorough rinsing (alternatively steam clean) and dry off. Remove residual contamination by scraping, surface grinding etc. Mechanically remove any unsound/incompatible coatings. Fully grind bare concrete to give an open sandpaper like surface. Reduce undulations/peaks etc by mechanical abrasion or grinding. Remove laitance by acid cleaning and subsequent rinsing. Best results are obtained when blasting the floor. Repair holes or large cracks with Pegacrete or 5180 Epoxy Repair Mortar (see PDS for details).

WSKAZÓWKI DOTYCZĄCE UŻYCIA

Stir thoroughly prior to use. Add the B component (hardener) to the base and stir mechanically. Mix the base to even consistency. Add the activator whilst stirring into the vortex and mix thoroughly, ensuring all activator material is worked away from the sides and the bottom and incorporated (use brush). Transfer the necessary amount to an empty clean, dry plastic can and mix further to ensure thorough blending.

WARUNKI APLIKACJI

Minimum 10°C. Provide air ventilation: open windows and doors.

APLIKACJA I ROZCIEŃCZANIE: PĘDZEL

Use undiluted.

APLIKACJA I ROZCIEŃCZANIE: WAŁEK

Do not dilute. Use a 12-15 mm polyamide roller.

APLIKACJA I ROZCIEŃCZANIE: PACA/KIELNIA

Spread out the necessary material over the surface and distribute evenly using a rake or trowel. Use a spike roller if necessary to de-aerate coating.

CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Rust-Oleum Thinner 160.

UWAGI

Do not apply to inadequately prepared or unsound surfaces. Do not apply as surface temperatures below 10°C or overnight ambient temperatures below 5°C. Low overnight temperatures may further extend minimum overcoating times. Overcoating should be carried out within the timescales above to promote maximum intercoat adhesion and avoid film defects. Ensure surfaces are clean between coats.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO:	198 g/l
Zawartość LZO w gotowej mieszaninie:	198 g/l
Kategoria LZO:	A/j
Limity LZO:	350 g/l
Uwagi dotyczące bezpieczeństwa:	Consult Safety Data Sheet and Safety Information printed on the can.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu