

RUST-OLEUM®
INDUSTRIAL



5421 EPOXY IMPREGNATION PRIMER

Rapid curing impregnation primer

- Overcoatable after just 4 hours: apply primer and topcoat in one day
- Easy all-in-1 packaging
- Impregnates porous and brittle floors
- Very low solvent content

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5421 EPOXY IMPREGNATION PRIMER

BESKRIVELSE

Rapid curing epoxy impregnation primer for porous floors.

ANBEFALT BRUK

New or untreated porous mineral surfaces, like concrete. Can be used in combination with all Rust-Oleum® epoxy and polyurethane coatings. Recoating time of only 4 hours.

TEKNISKE DATA

Tetthet:	1,1
Glansgrad:	Blank
Tørrestoffinnhold i vekt:	100%
Tørrestoffinnhold i volum:	100%
Blandeforhold:	Base : Activator = 3.3 : 1.7 (Volume)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	2 hours
Håndterbar:	3 hours
Overmalbar:	4 hours
Herdetid:	2 days
Brukstid:	30 minutes (do not leave in mixing can)

ANBEFALT VÅTFILMTYKKELSE

100 µm

ANBEFALT TØRRFILMTYKKELSE

100 µm

TEORETISK FORBRUK

10 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

New concrete should cure and dry for at least 30 days prior to the application of the product. Remove oil, grease and all other surface contaminations by alkaline or high pressure- (steam) cleaning in combination with appropriate detergents. Remove all laitance, loose or unsound concrete by vacuum-blasting or etching with Rust Surfa-Etch 108 Etching Solution. Remove concrete curing compounds completely. Large surfaces should preferably be prepared by abrasive blasting (vacuum blasting) or flame cleaning. Profile maximum 0,5 mm.

BRUKSANVISNING

Pour the liquid contents of the two small tins (resin and hardener) into the larger outer tin and mix thoroughly until uniform in colour. The mixed components must be decanted into a shallow roller tray and used immediately. If the mixed components are not decanted immediately, they will quickly become unusable and the mixing tin will become very hot and could pose a hazard.

PÅFØRINGSBETINGELSER

Temperature of air and substrate between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING & FORTYNNING: RULLE

Apply from the paint tray using a medium pile simulated sheepskin roller working well into the surface. A brush may be used for cutting in. Replace rollers and roller pan after 30 minutes. Use disposable rollers and roller pans.

RENGJØRING AV UTSTYR/SPILL

Immediately after use with Rust-Oleum® Thinner 160.

SIKKERHETSDATA

VOC nivå:	30 g/l
VOC ferdigblandet:	30 g/l
VOC kategori:	A/j
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can. Do not leave the mixed material in the can, because it can become very hot rapidly.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu