

RUST-OLEUM®
INDUSTRIAL



5500 SOLVENT-FREE EPOXY

High build epoxy for floors, metal and walls

- High build coating (150 microns), very durable
- Suitable for frequent (chemical) cleaning
- Resistant to oils and solvents
- As hard and dense as ceramic tiles



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5500 SOLVENT-FREE EPOXY

BESKRIVELSE

High build epoxy floor paint for garages, warehouses, showrooms, corridors, indoor car parks, workshops etc.

ANBEFALT BRUK

5500 is designed for application on concrete and masonry and can also be used on blasted steel, primarily intended for roller application and may also be applied by brush for small areas or touch-up only. A two coat 5500 System assures appropriate protection when in contact with chemicals (see chemical resistance guide), frequent chemical cleaning or high humidity and moisture conditions. Can be applied directly on properly cleaned, sound mineral substrates, sound, well prepared previous Epoxy coatings; porous substrates should be primed with 5401, 5401WB or 5421 Impregnation Primer; very dense substrates, like ceramic tiles, should be primed with Super Adhesive 3333 or 3366. 5500 can be applied directly on blasted steel or blasted galvanised steel; if required primed with RUST-OLEUM 9170/9180 Primer.

TEKNISKE DATA

Tetthet:	1,33
Glansgrad:	Blank
Tørrstoffinnhold i vekt:	100%
Tørrstoffinnhold i volum:	100%
Varmebestandig:	150°C (dry heat) - 50°C (immersion or wet heat)
Trykkfasthet:	50 MN/m ²
Strekkfasthet:	10 MN/m ²
Bøyefasthet:	70 MN/m ²
Blandeforhold:	Base : Activator = 2.54 : 1.46 (Volume)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	24 hours (20°C), 36 hours (10°C), 16 hours (30°C)
Håndterbar:	24 hours
Overmalbar:	After 24 hours, but within 72 hours
Herdetid:	10 days (14 days for immersion)
Brukstid:	60 minutes (20°C), 90 minutes (15°C), 150 minutes (10°C)
Induksjonstid:	15 minutes (20°C), 30 minutes (15°C), 60 minutes (10°C)

ANBEFALT VÅTFILMTYKKELSE

150 µm

ANBEFALT TØRRFILMTYKKELSE

150 µm

TEORETISK FORBRUK

6,7 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application. **Concrete and masonry:** New concrete or masonry should dry and cure for at least 30 days before applying the coating system. Remove laitance, loose and unsound concrete or deteriorated coatings preferably by abrasive blasting and repair surface defects with 5180 Epoxy Repair Mortar or Epoxy Putty 5412. Very dense and smooth concrete should be abrasive blasted or primed with Super Adhesive 3333 or 3366.

Steel: Remove loose rust, rust scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 100 µm. For immersion purposes, prepare to Sa 3 (ISO 8501-01 : 1988), blast profile max. 75 µm.

BRUKSANVISNING

These products are supplied in pre-measured 'units' consisting of one can of pigmented base material and one can of activator (5501). Stir individual components thoroughly before mixing them together. Add activator to base material and mix thoroughly with a low speed mixer.

PÅFØRINGSBETINGELSER

Temperature of material between 10 and 20°C, air and substrate between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING & FORTYNNING: PENSEL

Thinning not recommended. Use natural bristles, longhair brushes. Preferably use disposable brushes.

PÅFØRING & FORTYNNING: RULLE

Thinning not recommended. Use medium nap, 12 mm polyester rollers. For textured surfaces use long nap 14-18 mm rollers. Preferably use disposable rollers.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Not recommended.

RENGJØRING AV UTSTYR/SPILL

Use RUST-OLEUM Thinner 160.

MERKNADER

Maximum dry film thickness per coat: 300 µm dry, equals 300 µm wet. In time the product can show some yellowing. Apply the coating in strokes in one direction; do not use a cross-lap technique. Do not try to brush out the coating; lay it on thickly. 5500 cannot be used for swimming pools. For other immersion purposes, please always contact our Technical Service department."

SIKKERHETSDATA

VOC nivå:	155 g/l
VOC ferdigblandet:	155 g/l
VOC kategori:	A/j
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

5500 SOLVENT-FREE EPOXY

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu