

RUST-OLEUM®
— INDUSTRIAL —



5500 HIGH BUILD EPOXY

High build epoxy for floors, metal and walls

- High build coating (150 microns), very durable
- Suitable for frequent (chemical) cleaning
- Resistant to oils and solvents
- As hard and dense as ceramic tiles



footer_main_page_line_one

footer_main_page_line_two

5500 HIGH BUILD EPOXY

POPIS PRODUKTU (DLHÝ)

High build epoxy floor paint for garages, warehouses, showrooms, corridors, indoor car parks, workshops etc.

ODPORÚČANÉ POUŽITIE

5500 is designed for application on concrete and masonry and can also be used on blasted steel, primarily intended for roller application and may also be applied by brush for small areas or touch-up only. A two coat 5500 System assures appropriate protection when in contact with chemicals (see chemical resistance guide), frequent chemical cleaning or high humidity and moisture conditions. Can be applied directly on properly cleaned, sound mineral substrates, sound, well prepared previous Epoxy coatings; porous substrates should be primed with 5401, 5401WB or 5421 Impregnation Primer; very dense substrates, like ceramic tiles, should be primed with Super Adhesive 3333 or 3366. 5500 can be applied directly on blasted steel or blasted galvanised steel; if required primed with RUST-OLEUM 9170/9180 Primer.

TECHNICAL DATA

Hustota (g/cm ³):	1,33
Úroveň lesku:	Gloss
Obsah pevných látok v hmotnosti:	100%
Obsah pevných látok v objeme:	100%
Tepelná odolnosť:	150°C (dry heat) - 50°C (immersion or wet heat)
Pevnosť v tlaku:	50 MN/m ²
Pevnosť v ťahu:	10 MN/m ²
Pevnosť v ohybe:	70 MN/m ²
Pomer miešania:	Base : Activator = 2.54 : 1.46 (Volume)

DRY TIMES BY 20

Na dotyk suché:	24 hours (20°C), 36 hours (10°C), 16 hours (30°C)
Suché na manipuláciu:	24 hours
Suchý na opätovné natieranie:	After 24 hours, but within 72 hours
Úplne vytvrdnuté:	10 days (14 days for immersion)
Život v hmci:	60 minutes (20°C), 90 minutes (15°C), 150 minutes (10°C)
Indukčný čas:	15 minutes (20°C), 30 minutes (15°C), 60 minutes (10°C)

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

150 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

150 µm

TEORETICKÁ SPOTREBA

6,7 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application. **Concrete and masonry:** New concrete or masonry should dry and cure for at least 30 days before applying the coating system. Remove laitance, loose and unsound concrete or deteriorated coatings preferably by abrasive blasting and repair surface defects with 5180 Epoxy Repair Mortar or Epoxy Putty 5412. Very dense and smooth concrete should be abrasive blasted or primed with Super Adhesive 3333 or 3366.

Steel: Remove loose rust, rust scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 100 µm. For immersion purposes, prepare to Sa 3 (ISO 8501-01 : 1988), blast profile max. 75 µm.

NÁVOD NA POUŽITIE

These products are supplied in pre-measured 'units' consisting of one can of pigmented base material and one can of activator (5501). Stir individual components thoroughly before mixing them together. Add activator to base material and mix thoroughly with a low speed mixer.

PODMIENKY APLIKÁCIE

Temperature of material between 10 and 20°C, air and substrate between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Thinning not recommended. Use natural bristles, longhair brushes. Preferably use disposable brushes.

APLIKÁCIA A RIEDENIE: VALEC

Thinning not recommended. Use medium nap, 12 mm polyester rollers. For textured surfaces use long nap 14-18 mm rollers. Preferably use disposable rollers.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Use RUST-OLEUM Thinner 160.

POZNÁMKY

Maximum dry film thickness per coat: 300 µm dry, equals 300 µm wet. In time the product can show some yellowing. Apply the coating in strokes in one direction; do not use a cross-lap technique. Do not try to brush out the coating; lay it on thickly. 5500 cannot be used for swimming pools. For other immersion purposes, please always contact our Technical Service department."

DATA SAFETY DATA

Úroveň VOC:	155 g/l
VOC ready mix:	155 g/l
Kategória VOC:	A/j
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

5500 HIGH BUILD EPOXY

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu