

RUST-OLEUM®
INDUSTRIAL



5800 EPOXY RAPID WB

Rapid curing water-based epoxy

- Durable epoxy floor
- Can be recoated after just 3 hours
- Available in matt or gloss finish
- Water-based, very low odour
- Excellent flow and smooth finish



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5800 EPOXY RAPID WB

BESKRIVNING

Rapid curing epoxy floor paint for inside use. For garages, warehouses, showrooms, corridors, indoor car parks, workshops etc.

REKOMMENDERAD ANVÄNDNING

5800 Epoxy Rapid WB can be applied on cleaned, sound mineral substrates, sound and well prepared previous coatings. The product can be applied directly on porous substrates; a special primer is not needed.

TEKNISK DATA

Densitet:	1,2
Glansnivå:	Glans, Matt
Glansnivå vid 60°:	85 - 95% (mixed with RO 5801) 0 -10% (mixed with RO 5802) at 45°
Torrsubstansvolym:	48%
Blandningsförhållande:	Base : Activator = 2 : 3 (Volume)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	2 hours
Hanteringstorr:	3 hours
Övermålningsbar:	After 3 hours, within 5 days
Fullt härdad:	7 days (traffic possible after 24 hours)
Brukstid:	2 hours

REKOMMENDERAD VÅTFILMSTJOCKLEK

167 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

80 µm

TEORETISK FÖRBRUKNING

6 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Concrete must be at least 30 days old, completely dry and free of surface laitance, contaminants and previous poorly bonded coatings. Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand previous coatings which are in good condition to remove gloss and to roughen the surface slightly, check compatibility. Very smooth concrete or concrete with surface laitance (a weak dusty layer) should be abraded or etched with Surfa-Etch 108 to ensure adequate adhesion. The concrete should be thoroughly washed down and allowed to dry after. Powerfloat Epoxy Floor Primer 3366 is recommended on powerfloated surfaces.

BRUKSANVISNING

Stir base thoroughly before adding it to the activator. Again stir the mixture thoroughly until an even colour and consistency are obtained. Do not mix more material than can be applied in 2 hours.

Higher temperatures will reduce the pot life.

APPLICERINGSFÖRHÅLLANDEN

Apply only if the temperature of the surface and environment is between 10 and 30 °C and relative humidity is below 85%.

APPLICERING OCH SPÅDNING: PENSEL

Use natural bristles, long hair brushes.

APPLICERING OCH SPÅDNING: ROLLER

Apply with a medium pile simulated sheepskin roller, working well into the surface of the concrete. Thin if required with water, the product will darken slightly as curing commences and it should not be over rolled.

RENGÖRING AV UTRUSTNING/SPILL

Immediately after use with warm soapy water.

ANMÄRKNINGAR

For a glossy finish mix the base component with 5801 Epoxy Rapid Activator Gloss. For a matt finish mix the base component with 5802 Epoxy Rapid Activator Matt. If the product is used outside it is required to finish with a Polyurethane Topcoat such as Rust-O-Thane 9200 (do not use a clear coat).

SÄKERHETSDATA

VOC-nivå:	65 g/l
VOC färdigmix:	65 g/l
VOC-kategori:	A/j
VOC-gräns:	140 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 15° and 25°C.

Keep from freezing.

Utgivningsdatum: 10/03/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaper i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu