

RUST-OLEUM®
INDUSTRIAL



7100 FLOOR COATING



Easy to apply 1 component floor coating

- Single pack, solvent based floor coating
- For foot traffic, interior and exterior
- For old concrete floors (>2 yrs), metal and wood
- High gloss appearance, great hiding power
- Touch dry after 6 hours (at 20°C)

footer_main_page_line_one

footer_main_page_line_two

7100 FLOOR COATING

POPIS PRODUKTU (DLHÝ)

Easy to apply solvent based Alkyd floor coating specially designed for applying on old (>2 years), dry concrete for interior and exterior use. The coating has a good resistance against abrasion and neutral detergents (no alkaline cleaning agents) and is resistance during short contact periods against lubricating oils, fuel, petrol etc.

ODPORÚČANÉ POUŽITIE

7100 Floor Coating can be applied on concrete floors older than 2 years, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a damp repellent additive, which will prevent a good adhesion. 7100 Floor Coating can also be applied on old good adhering coatings. 7100 can be applied onto metal floors which have been correctly prepared and primed with a suitable Rust-Oleum metal primer.

TECHNICAL_DATA

Hustota (g/cm³): 1,0 - 1,1 kg/l
Úroveň lesku: Gloss
Obsah pevných látok v objeme: 36 - 40 %

DRY_TIMES_BY_20

Na dotyk suché: 6 hours
Suchý na opätovné natieranie: 24 hours
Úplne vytvrdnuté: 1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

130 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

50 µm

TEORETICKÁ SPOTREBA

8,0 m²/l at 50 µm dry

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove oil, grease and other contaminations with Rust-Oleum 2901 EpoxyShield Cleaner/Degreaser for floors or high pressure- (steam) cleaning in combination with appropriate detergents. Sand old intact coatings to roughen the surface in order to establish a good adhesion. Check the compatibility with old intact coatings. During application the surface should be dry and clean. On porous concrete a first coat should be applied with 7100 diluted with an addition of approximately 10% volume 7301. Remove curing compounds by means of dust free blasting.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area.

APLIKÁCIA A RIEDENIE: ŠTETEC

Sparingly, if required, with 10% volume 7301.

APLIKÁCIA A RIEDENIE: VALEC

Sparingly, if required, with 10% volume 7301. In case of roller application it can be necessary to apply 2 coats in order to obtain the recommended film thickness.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Immediately after application using 7301.

POZNÁMKY

Apply 7100 Floor Coating never on alkaline substrates.

DATA SAFETY DATA

Úroveň VOC: 456 g/l
VOC readymix: 485 g/l
Kategória VOC: A/i
Limit VOC: 500 g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu