

RUST-OLEUM®
INDUSTRIAL



7200 FLOORCOAT PU

Durable floor paint in any gloss or satin colour



- Extra durable because of polyurethane addition
- Tintable in any colour in gloss or satin finish
- Excellent flow; easy to apply
- For use on concrete, wood, masonry and pre-painted floors
- Also ideal for line marking

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

7200 FLOORCOAT PU

BESKRIVELSE

Hard-wearing, easy to apply single pack floor coating with PU addition.

ANBEFALT BRUK

Floorcoat PU (7200) can be applied directly on interior or exterior concrete floors (see surface preparation), wooden floors and masonry which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a damp repellent additive, which will prevent a good adhesion. Floorcoat PU (7200) can also be applied on old good adhering coatings and can also be applied onto metal floors which have been correctly prepared and primed with a suitable Rust-Oleum metal primer.

TEKNISKE DATA

Tetthet:	1,1
Glansgrad:	Blank,Satinert
Tørrestoffinnhold i volum:	45%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	4 hours
Håndterbar:	8 hours
Overmalbar:	24 hours
Herdetid:	1 week

ANBEFALT VÅTFILMTYKKELSE

110 µm

ANBEFALT TØRRFILMTYKKELSE

50 µm

TEORETISK FORBRUK

9 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove oil, grease and other contaminations with Rust-Oleum ND14 Cleaner/Degreaser or high pressure (steam) cleaning in combination with appropriate detergents. Sand old intact coatings to roughen the surface in order to establish a good adhesion. Check the compatibility with old intact coatings. During application the surface should be dry and clean. On porous concrete a first coat should be applied with 7200 diluted with ± 5% Thinner 633. Ensure concrete is at least 28 days old and moisture content lower than 6%. Remove curing compounds by means of dust free blasting or acid etching with Rust-Oleum SE108.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Apply in a dry and well-ventilated area.

PÅFØRING & FORTYNNING: PENSEL

Dilute sparingly, if required, with 5% volume Thinner 633.

PÅFØRING & FORTYNNING: RULLE

Dilute sparingly, if required, with 5% volume Thinner 633. In case of roller application it can be necessary to apply 2 coats in order to obtain the recommended film thickness.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Thin with max. 10% volume Thinner 641. Gravity cup and pressure cup. Tip size: 1.0 -1.5 mm. Atomising pressure: 2 – 4 bar.

RENGJØRING AV UTSTYR/SPILL

Immediately after application with Thinner 633.

MERKNADER

Do not apply Floorcoat PU (7200) on highly alkaline substrates, or in areas which will be constantly under water.

SIKKERHETSDATA

VOC nivå:	450 g/l
VOC ferdigblandet:	495 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu