



# **7200NS FLOORCOAT PU**

# Single pack anti-slip floor coating

- · For foot traffic, interior and exterior
- Anti-slip additive is premixed in the coating
- For use on concrete (>2yrs), metal and wood
- · Touch dry after 4 hours
- · Apply a 2nd coat to increase the antislip properties

# KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 7200NS FLOORCOAT PU

#### DESCRIPTION

Anti-slip polyurethane-modified floor coating, abrasion resistant and easy to apply. 1K

#### RECOMMENDED USE

Floorcoat PU 7200NS can be applied directly on interior or exterior concrete floors (see surface preparation), wooden floors and masonry which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a damp repellent additive, which will prevent a good adhesion. Floorcoat PU (7200NS) can also be applied on old good adhering coatings and can also be applied onto metal floors which have been correctly prepared and primed with a suitable Rust-Oleum metal primer.

#### **TECHNICAL DATA**

Density (g/cm³): 0,9-1,2 Solids content in volume: 45%

## DRY TIMES BY 20° C/RH 50%

 Touch dry:
 4h

 Dry to handle:
 8h

 Dry to recoat:
 24h

 Fully cured:
 1 week

## RECOMMENDED WET FILM THICKNESS

110 µm

## RECOMMENDED DRY FILM THICKNESS

50 µm

#### THEORETICAL CONSUMPTION

9 m<sup>2</sup>/l

#### PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

#### **SURFACE PREPARATION**

Remove oil, grease and other contaminations with Rust-Oleum ND14 Cleaner/Degreaser or high pressure (steam) cleaning in combination with appropriate detergents. Sand old intact coatings to roughen the surface in order to establish a good adhesion. Check the compatibility with old intact coatings. During application the surface should be dry and clean. On porous concrete a first coat should be applied with 7200NS diluted with  $\pm\,5\%$  Thinner 633. Ensure concrete is at least 28 days old and moisture content lower than 6%. Remove curing compounds by means of dust free blasting or acid etching with Rust-Oleum SE108.

# **DIRECTIONS FOR USE**

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

# **APPLICATION CONDITIONS**

Apply in a dry and well-ventilated area.

# **APPLICATION & THINNING: BRUSH**

Dilute sparingly, if required, with 5% volume Thinner 633.

# **APPLICATION & THINNING: ROLLER**

Dilute sparingly, if required, with 5% volume Thinner 633. In case of roller application it can be necessary to apply 2 coats in order to obtain the recommended film thickness.

#### **CLEANING OF EQUIPMENT / SPILLS**

Immediately after application with Thinner 633.

#### REMARKS

Do not apply Floorcoat PU (7200NS) on highly alkaline substrates, or in areas which will be constantly under water.

#### SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between  $5^{\circ}$  and  $35^{\circ}$ C.

**Date issued:** 12/07/2024

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T: +31 (0) 165 593 606 F: +31 (0) 165 593 600 intr@mist-oleum eu Tor Coatings Ltd (Rust-Oleum Industrial Shadon Way, Portobello Ind. Estate Birtley, Chester-le-Street DH3 2RE United Kingdom T: +44 (0)1914 113 146 F: +44 (0)1914 113 147 info@rust-oleum.eu

38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu

