

**RUST-OLEUM®**  
— INDUSTRIAL —



## 769® DAMP-PROOF RUST PRIMER

# Single pack metal primer based on fish oil

- Requires minimal surface preparation
- Penetrates deep into the rust for optimal protection
- Expels moisture & air from the surface
- Can be applied on slightly damp surfaces
- Unique proven formula based on fish oil since 1921

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# 769® DAMP-PROOF RUST PRIMER

## POPIS PRODUKTU (DLOUHÝ)

Single pack rust primer based on a fish oil containing alkyd for direct application on slightly moist or dry metal surfaces. Proven formula since 1921!

## DOPORUČENÉ POUŽITÍ

769 is specially developed to be applied on hand tool prepared sound rusted steel surfaces. Can be applied on slightly damp surfaces and provides protection under C4 exposure (ISO 12944) conditions with system:

- 769
- 1060 or 1080
- Alkythane® 7500

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,33
Úroveň lesku:	Matt
Obsah pevných látek v objemu:	50%
Tepelná odolnost:	120°C (dry heat)

## DRY TIMES BY 20

Dotykem suché:	4 hours
Suché na manipulaci:	8 hours
Suchý nátěr:	After 24 hours
Plně vytvrzené:	8 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

70 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 µm

## TEORETICKÁ SPOTŘEBA

14,5 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations with Rust-Oleum ND14 cleaner or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 2 (ISO 8501-1: 1988), light blast cleaning or sanding. Sand previous coatings, which are in good condition to roughen the surface slightly. The surface must be clean and preferably dry during application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Dilute up to 10% volume RUST-OLEUM Thinner 633.  
Use natural bristles, long hair brushes.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Dilute up to 10% volume RUST-OLEUM Thinner 633.  
Use medium nap, polyamide 8 -12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

If required, up to 5% volume RUST-OLEUM Thinner 641.  
Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch Fluid pressure: 130 - 200 bar.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

10-20% volume RUST-OLEUM Thinner 641.  
Gravity cup and pressure cup. Tip size: 1.2 -1.8 mm. Atomising pressure: 2 - 4 bar.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Use RUST-OLEUM Thinner 160 or mineral spirits.

## POZNÁMKY

Maximum dry film thickness per coat: 60 µm dry, equals 120 µm wet.

## DATA SAFETY DATA

Úroveň těkavých organických látek:	375 g/l
VOC readymix:	456 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu