

RUST-OLEUM®
INDUSTRIAL



8300 HYGIENIC WALL COATING

Fast drying wall paint for humid areas

- Offers protection against mild chemical exposure, humidity and moisture
- Can be applied as low as -10°C
- Non-yellowing and resistant to frequent cleaning
- Very fast drying and recoating times
- Contains a biocide to protect the dried coating against fungal degradation

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

8300 HYGIENIC WALL COATING

BESKRIVNING

Single pack hygienic topcoat protects against mild chemical exposure, occasional product spillage, frequent chemical cleaning, intermittent high humidity and moisture.

REKOMMENDERAD ANVÄNDNING

8300 Topcoats should be applied on mineral substrates primed with Primer 8399. Resists mild chemical exposure, occasional product spillage, frequent chemical cleaning, intermittent high humidity and moisture. Can be applied on 8399 or well prepared previous coatings. 8300 is classified Class 1 Surface Spread of Flame according to BS 476; part 7 : 1987.

TEKNISK DATA

Densitet:	1,18
Glansnivå:	Glans
Torrsubstansvolym:	42%
Värmebeständighet:	80°C (dry heat)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	2 hours (20°C), 4 hours (10°C), 30 minutes (30°C), 6 hours (0°C), 8 hours (-10°C)
Hanteringstorr:	4 hours (20°C), 6 hours (10°C), 1 hour (30°C), 8 hours (0°C), 12 hours (-10°C)
Övermålningsbar:	6 hours (20°C), 12 hours (10°C), 2 hours (30°C), 16 hours (0°C), 24 hours (-10°C)
Fullt härdad:	8 days (20°C), 12 days (10°C), 5 days (30°C)

REKOMMENDERAD VÅTFILMSTJOCKLEK

85 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

35 µm

TEORETISK FÖRBRUKNING

12 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

New concrete, plastered or brick surfaces should cure and dry for at least 30 days prior to the application of coatings. Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning. Wash total surface with plenty of fresh/warm water or high pressure (steam) cleaning in order to remove all remnants of contamination and cleaners ND14 or FK111. Sand previous coatings, which are in good condition to remove gloss and to roughen the surface slightly. Remove non-adhering old coatings. The surface must be clean and dry during application.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Temperature of air, substrate and coating material between -10° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point. Below 0°C the surface should be free from ice.

APPLICERING OCH SPÅDNING: PENSEL

-10 to 5°C: 10-15% volume RUST-OLEUM Thinner 633.
> 5°C: Up to 10% volume RUST-OLEUM Thinner 633. Use brushes based on a mixture of synthetic/natural bristles.

APPLICERING OCH SPÅDNING: ROLLER

-10 to 5°C: 10-15% volume RUST-OLEUM Thinner 633.
> 5°C: Up to 10% volume RUST-OLEUM Thinner 633. Use medium nap polyamide 8-12 mm rollers. Roller application may require 2 coats to achieve recommended d.f.t.

APPLICERING OCH SPÅDNING: AIRLESSPRUTA

-10 to 5°C: Up to 10% volume RUST-OLEUM Thinner 160.
> 5°C: up to 15% volume RUST-OLEUM Thinner 633. Pneumatic and electric airless equipment. Tip size: 0.011-0.017 inch. Fluid pressure: 150 - 200 bar. Low temperatures may affect the atomising properties.

APPLICERING OCH SPÅDNING: TRYCKLUFTSSPRUTA

-10 to 5°C: Up to 10% volume RUST-OLEUM Thinner 160.
> 5°C 10-15% volume RUST-OLEUM Thinner 633. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomising pressure: 2 - 4 bar.

RENGÖRING AV UTRUSTNING/SPILL

Use RUST-OLEUM Thinner 160.

ANMÄRKNINGAR

Maximum dry film thickness per coat: 60 µm dry, equals 145 µm wet. Direct contact with oils, fats and greases can soften the coating.

SÄKERHETSDATA

VOC-nivå:	458 g/l
VOC färdigmix:	499 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu