

**RUST-OLEUM®**  
INDUSTRIAL



## 8399 HYGIENIC PRIMER

# Single pack hygienic primer

- Very fast drying and recoatable with 8300 hygienic topcoat
- Offers protection against mild chemical exposure, occasional product spillage, frequent chemical cleaning, intermittent high humidity and moisture
- Can be applied as low as -10 °C ; ideal for refrigerated areas
- Non-yellowing and resistant to frequent cleaning

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 8399 HYGIENIC PRIMER

## BESKRIVELSE

Single pack hygienic primer protects (with 8300) against mild chemical exposure, occasional product spillage, frequent chemical cleaning, humidity and moisture. For walls and ceilings.

## ANBEFALT BRUK

8399 should be used on mineral substrates like concrete, brick and plastered walls, masonry and mineral fibre board. 8399 Primer should be recoated with 8300 Topcoat(s); they resist mild chemical exposure, occasional product spillage, frequent chemical cleaning, intermittent high humidity and moisture. Can be applied on cleaned, sound mineral substrates and sound, well prepared previous coatings; porous substrates should be primed with diluted 8399. Classified Class 1 Surface Spread of Flame according to BS 476; part 7 : 1987.

## TEKNISKE DATA

Tetthet:	1.36
Glansgrad:	Matt
Tørrestoffinnhold i volum:	43.5 %
Varmebestandig:	80 °C (dry heat)

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 h (20°C), 2 h (10°C), 10 min (30°C), 4 h (0°C), 6 h (-10°C)
Håndterbar:	2 h (20°C), 4 h (10°C), 30 min (30°C), 6 h (0°C), 8 h (-10°C)
Overmalbar:	3 h (20°C), 6 h (10°C), 1 h (30°C), 8 h (0°C), 12 h (-10°C)
Herdetid:	8 days (20°C), 12 days (10°C), 5 days (30°C)

## ANBEFALT VÅTFILMTYKKELSE

80 µm

## ANBEFALT TØRRFILMTYKKELSE

35 µm

## TEORETISK FORBRUK

12.4 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

New concrete, plastered or brick surfaces should cure and dry for at least 30 days prior to the application of coatings. Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning. (With ND14 or FK111) Wash total surface with plenty of fresh/warm water or high pressure (steam) cleaning in order to remove all remnants of contamination and cleaners. Sand previous coatings, which are in good condition to remove gloss and to roughen the surface slightly. Remove non-adhering old coatings. The surface must be clean and dry during application.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between -10° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point. Below 0°C the surface should be free from ice.

## PÅFØRING & FORTYNNING: PENSEL

-10 to 5°C : 10-20 vol. %; RUST-OLEUM Thinner 633.  
> 5°C : Up to 5 vol. %; RUST-OLEUM Thinner 633. Use brushes based on a mixture of synthetic/natural bristles.

## PÅFØRING & FORTYNNING: RULLE

-10 to 5°C : 10-20 vol. %; RUST-OLEUM Thinner 633.  
> 5°C : Up to 5 vol. %; RUST-OLEUM Thinner 633. Use medium nap polyamide (perlon 8-12 mm.) rollers. Roller application may require 2 coats to achieve recommended d.f.t.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

-10 to 5°C : Up to 15 vol. %; RUST-OLEUM Thinner 160.  
> 5°C : up to 10 vol. %; RUST-OLEUM Thinner 633. Pneumatic and electric airless equipment. Tip size: 0.015-0.021 inch. Fluid pressure: 150 - 200 bar. Low temperatures may affect the atomising properties.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

-10 to 5°C : Up to 15 vol. %; RUST-OLEUM Thinner 160.  
> 5°C 10-20 vol. %; RUST-OLEUM Thinner 633. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomising pressure: 2 - 4 bar.r.

## RENGJØRING AV UTSTYR/SPILL

RUST-OLEUM Thinner 160

## MERKNADER

Maximum dry film thickness per coat: 60 µm dry, equals 165 µm wet. Direct contact with oils, fats and greases can soften the coating.

## SIKKERHETSDATA

VOC nivå:	440 g/l
VOC ferdigblandet:	499 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)