

RUST-OLEUM®
INDUSTRIAL



8399 HYGIENIC PRIMER

Single pack hygienic primer

- Very fast drying and recoatable with 8300 hygienic topcoat
- Offers protection against mild chemical exposure, occasional product spillage, frequent chemical cleaning, intermittent high humidity and moisture
- Can be applied as low as -10 °C ; ideal for refrigerated areas
- Non-yellowing and resistant to frequent cleaning

footer_main_page_line_one

footer_main_page_line_two

8399 HYGIENIC PRIMER

POPIS PRODUKTU (DLHÝ)

Single pack hygienic primer protects (with 8300) against mild chemical exposure, occasional product spillage, frequent chemical cleaning, humidity and moisture. For walls and ceilings.

ODPORÚČANÉ POUŽITIE

8399 should be used on mineral substrates like concrete, brick and plastered walls, masonry and mineral fibre board. 8399 Primer should be recoated with 8300 Topcoat(s); they resist mild chemical exposure, occasional product spillage, frequent chemical cleaning, intermittent high humidity and moisture. Can be applied on cleaned, sound mineral substrates and sound, well prepared previous coatings; porous substrates should be primed with diluted 8399. Classified Class 1 Surface Spread of Flame according to BS 476; part 7 : 1987.

TECHNICAL DATA

Hustota (g/cm ³):	1.36
Úroveň lesku:	Matt
Obsah pevných látok v objeme:	43.5 %
Tepelná odolnosť:	80 °C (dry heat)

DRY TIMES BY 20

Na dotyk suché:	1 h (20°C), 2 h (10°C), 10 min (30°C), 4 h (0°C), 6 h (-10°C)
Suché na manipuláciu:	2 h (20°C), 4 h (10°C), 30 min (30°C), 6 h (0°C), 8 h (-10°C)
Suchý na opätovné natieranie:	3 h (20°C), 6 h (10°C), 1 h (30°C), 8 h (0°C), 12 h (-10°C)
Úplne vytvrdnuté:	8 days (20°C), 12 days (10°C), 5 days (30°C)

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

80 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTREBA

12.4 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

New concrete, plastered or brick surfaces should cure and dry for at least 30 days prior to the application of coatings. Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning. (With ND14 or FK111) Wash total surface with plenty of fresh/warm water or high pressure (steam) cleaning in order to remove all remnants of contamination and cleaners. Sand previous coatings, which are in good condition to remove gloss and to roughen the surface slightly. Remove non-adhering old coatings. The surface must be clean and dry during application.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between -10° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point. Below 0°C the surface should be free from ice.

APLIKÁCIA A RIEDENIE: ŠTETEC

-10 to 5°C : 10-20 vol. %; RUST-OLEUM Thinner 633.
> 5°C : Up to 5 vol. %; RUST-OLEUM Thinner 633. Use brushes based on a mixture of synthetic/natural bristles.

APLIKÁCIA A RIEDENIE: VALEC

-10 to 5°C : 10-20 vol. %; RUST-OLEUM Thinner 633.
> 5°C : Up to 5 vol. %; RUST-OLEUM Thinner 633. Use medium nap polyamide (perlon 8-12 mm.) rollers. Roller application may require 2 coats to achieve recommended d.f.t.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

-10 to 5°C : Up to 15 vol. %; RUST-OLEUM Thinner 160.
> 5°C : up to 10 vol. %; RUST-OLEUM Thinner 633. Pneumatic and electric airless equipment. Tip size: 0.015-0.021 inch. Fluid pressure: 150 - 200 bar. Low temperatures may affect the atomising properties.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

-10 to 5°C : Up to 15 vol. %; RUST-OLEUM Thinner 160.
> 5°C 10-20 vol. %; RUST-OLEUM Thinner 633. Gravity cup and pressure cup. Tip size: 1.2 -1.8 mm. Atomising pressure: 2 - 4 bar.r.

ČISTENIE ZARIADENIA / POSTRIEKANIE

RUST-OLEUM Thinner 160

POZNÁMKY

Maximum dry film thickness per coat: 60 µm dry, equals 165 µm wet. Direct contact with oils, fats and greases can soften the coating.

DATA SAFETY DATA

Úroveň VOC:	440 g/l
VOC readymix:	499 g/l
Kategória VOC:	A/i
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu