

RUST-OLEUM®
INDUSTRIAL



8700 HYGIENIC WALL COATING

Quick drying water-based hygienic wall paint

- Offers better protection against contamination than non-hygienic paint
- Very fast drying and recoating times (3 coats in a day)
- Contains a biocide to protect the dried coating against fungal degradation
- Can be applied on damp surfaces in combination with 8798 hygienic primer
- Durable and washable gloss finish

footer_main_page_line_one

footer_main_page_line_two

8700 HYGIENIC WALL COATING

POPIS PRODUKTU (DLHÝ)

Water-based single pack hygienic paint protects against normal humidity and contamination indoors. Suitable for walls and ceilings.

ODPORÚČANÉ POUŽITIE

Hygienic Topcoat 8700 are developed to be applied on mineral surfaces primed with White Masonry Sealer 8798 or directly on previous coated substrates. 8700 will resist normal humidity and should be applied over 8798 in humid conditions.

TECHNICAL DATA

Hustota (g/cm ³):	1,2
Úroveň lesku:	Gloss
Obsah pevných látok v objeme:	35%
Tepelná odolnosť:	80°C (dry heat)

DRY TIMES BY 20

Na dotyk suché:	30 minutes (20°C), 2 hours (10°C), 15 minutes (30°C)
Suché na manipuláciu:	2 hours (20°C), 6 hours (10°C), 2 hours (30°C)
Suchý na opätovné natieranie:	2 hours (20°C), 16 hours (10°C), 2 hours (30°C)
Úplne vytvrdnuté:	3 days (20°C), 5 days (10°C), 2 days (30°C)

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTREBA

10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove contamination with FK111 or ND14. Wash total surface with plenty of fresh/warm water or high pressure (steam) cleaning in order to remove all remnants of contamination and cleaners. Prime or spot-prime with White Masonry Sealer 8798. Sand intact coatings to roughen the surface slightly. The surface must be clean and may be slightly damp during application.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 75%. The substrate temperature must be at least 5°C above dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Up to 5% volume with water. Use brushes based on a mixture of synthetic/natural bristles.

APLIKÁCIA A RIEDENIE: VALEC

Up to 5% volume with water. Use medium nap, 8-12 mm, woven acrylic or polyester rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

If required up to 5% volume with water. Pneumatic and electric airless equipment. Tip size: 0.015-0.018 inch. Fluid pressure: 150 - 225 bar. Check wet film thickness, avoid excessive film thickness.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

5 - 10% volume with water. Gravity cup and pressure cup. Tip size: 1.2 -1.8 mm. Atomising pressure: 2 - 4 bar.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Immediately after use with water and soap.

POZNÁMKY

Maximum dry film thickness per coat: 80 µm dry, equals 225 µm wet. On very porous substrates it is advisable to dilute the first coat up to 50% with water, followed by a second coat.

DATA SAFETY DATA

Úroveň VOC:	87 g/l
VOC readymix:	87 g/l
Kategória VOC:	A/b
Limit VOC:	100 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C. **Keep from freezing.**

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu