

**RUST-OLEUM®**  
INDUSTRIAL



## 8798 HYGIENIC PRIMER

# Water-based single pack hygienic primer

- Fast drying and recoatable with 8700
- Offers better protection against contamination than non-hygienic paint
- Water-based paint
- Multiple coatings in one day possible
- Can be applied on damp surfaces

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# 8798 HYGIENIC PRIMER

## POPIS PRODUKTU (DLOUHÝ)

Water-based single pack rapid curing hygienic primer protects (with 8700) against normal humidity and contamination indoors and outdoors. Suitable for walls and ceilings.

## DOPORUČENÉ POUŽITÍ

8798 should be used on mineral substrates like concrete, plaster, brickwork and masonry for interior- and exterior applications. 8798 will resist normal humidity and can be applied as a wall primer (diluted up to 30% with water), as a topcoat and can be recoated with 8700 Topcoat.

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	1.29
Úroveň lesku:	Satin
Obsah pevných látek v objemu:	35%
Tepelná odolnost:	90 °C (dry heat)

## DRY\_TIMES\_BY\_20

Dotykem suché:	30 min (20°C), 2 h (10°C), 30 min (30°C)
Suché na manipulaci:	2 h (20°C), 4 h (10°C), 1 h (30°C)
Suchý nátěr:	4 h (20°C), 6 h (10°C), 3 h (30°C)
Plně vytvrzené:	3 days (20°C), 5 days (10°C), 2 days (30°C)

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

40 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

115 µm

## TEORETICKÁ SPOTŘEBA

9 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure- (steam) cleaning in combination with appropriate detergents. New concrete, plaster or brick surfaces should cure and dry for at least 30 days prior to application of the coating. Repair surface defects. Remove contamination with RUST-OLEUM FK111 or ND14. Wash total surface with plenty of fresh/warm water or high pressure- (steam) cleaning in order to remove all remnants of contamination and cleaners. Remove deteriorated coatings by scraping and wire brushing. Sand intact coatings to roughen the surface slightly. The surface must be clean and may be slightly damp during application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 75%. The substrate temperature must be at least 5°C above dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Up to 5 vol. % water. Use brushes based on a mixture of synthetic/natural bristles.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Up to 5 vol. % water. Use medium nap, 8-12 mm, woven acrylic or polyester rollers. For textured surfaces use long nap 14-18 mm rollers.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

If required 5 vol. % with water. Pneumatic and electric airless equipment. Tip size: 0.017-0.024 inch Fluid pressure: 130 - 200 bar. Check wet film thickness, avoid excessive film thickness.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Immediately after use with water and soap.

## POZNÁMKY

Maximum dry film thickness per coat: 100 µm dry, equals 285 µm wet. On very porous substrates it is advisable to dilute the first coat up to 30% with water, followed by a second coat.

## DATA\_SAFETY\_DATA

Úroveň těkavých organických látek:	30 g/l
VOC readymix:	30 g/l
Kategorie VOC:	A/g
Limitní hodnota VOC:	50 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C. **Protect from freezing.**

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu