

**RUST-OLEUM®**  
INDUSTRIAL



## 9100 HIGH PERFORMANCE EPOXY

# High build 2 pack epoxy for floor and metals

- 2x thicker than regular epoxies (125 micron dry)
- Very resistant against abrasion and chemicals
- Contains a high amount of rust inhibitors
- Can be applied on metal and floors
- Tintable in almost any colour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 9100 HIGH PERFORMANCE EPOXY

## ОПИСАНИЕ

Two-pack, high layer thickness glossy epoxy, resistant to corrosion and chemicals, suitable for applications on metal or floors.

## ПРЕПОРЪЧАНА УПОТРЕБА

9100 high Performance can be applied on: manually prepared rusted steel surfaces, new, blasted, primed steel; concrete and previously compatible coated surfaces. 9100 Topcoats offer appropriate protection against strong chemicals, acids, alkalis and solvents; frequent product spillage and chemical cleaning; high humidity and moisture conditions.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

Topcoat: for U.V. resistance: polyurethane Topcoats 9200 or 9600 should be applied (except for the clear coatings).

Primers: porous mineral substrates: 5401 or 5421 Impregnation Primer.

Very dense substrates, like ceramic tiles: Super Adhesive 3333.

9100 Topcoats can be applied on 9169, 9170 and 9180 Metal Primers.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см <sup>3</sup> ):	1,32
Гланцово ниво:	gloss
corrosion_class:	c4_high
Съдържание на твърди вещества в обема:	89,3 %
heat_resistance:	Immersion or wet heat: 50°C - Dry Heat: 100°C
Степен на смесване:	Vol: 2:1

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	6 hours - 8 hours
Сух за употреба:	8 hours - 16 hours
Готов за повторно нанасяне:	After 16 hours
Напълно втвърден:	7 days
Живот в гърне:	90 minutes
Време за въвеждане:	-

## МОКЪР СЛОЙ

140 µm

## СУХ СЛОЙ

125 µm

## РАЗХОДНА НОРМА

7.15 m<sup>2</sup>/l

## КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove all dirt and contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergent like Rust-Oleum ND14. Sand previous glossy coatings to roughen the surface slightly, check compatibility. The surface must be clean and dry.

Steel: Remove loose rust, mill scale and deteriorated coatings by hand or power tool cleaning to St 2/3 (ISO 8501-01 : 1988). Blast large areas to Sa 2 (ISO 8501-01: 1988), blast profile max. 50 µm. For immersion purposes, prepare to Sa 3 (ISO 8501-01 : 1988), blast profile max. 75 µm.

Concrete and masonry: New concrete or masonry should cure for at least 30 days before applying the coating system. Remove laitance, any loose or unsound concrete or coatings. Smooth concrete should be abraded except in case of use of a Rust-Oleum adhesion primer.

## НАЧИН НА УПОТРЕБА

Stir individual components thoroughly before mixing them together, with a mechanical low speed mixer for 3 minutes.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and product between 0 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Use natural bristles, long hair preferably disposable brushes. Dilution not normally required but if necessary dilute up to 10% volume with Thinner 160. Dilution will result in the requirement of VOC <100g/l not being met.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Use a medium nap polyamide 14-20 mm roller. Roller application requires 2 coats to achieve recommended d.f.t. If necessary dilute up to 10% volume with Thinner 160. Dilution will result in the requirement of VOC <100g/l not being met.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Tip size 0.013-0.021 inch. Fluid pressure: 150 - 225 bar. Avoid excessive film thickness. Dilution not normally required but if necessary dilute up to 10% volume with Thinner 160. Dilution will result in the requirement of VOC <100g/l not being met.

## ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Not recommended.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

RUST-OLEUM Thinner 160.

## ЗАБЕЛЕЖКИ

Contact with water or chemicals can cause discolouration especially for colours made with tinting machine. Uses bases and activators from one same batch per project. The batch number is printed on the can.

For use on floors subjected to heavy abrasion, standard and medium colours are recommended. In the case of deep and/or bright tones (red, yellow, orange, green, blue etc) a clear polyurethane varnish should be applied.

Maximum dry film thickness per coat: 250µm

Дата на издаване: 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

# 9100 HIGH PERFORMANCE EPOXY

## ДАНИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 98,5 g/l  
Категория ЛОС: A/j  
Ограничение за ЛОС: 500 g/l  
Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

## СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)