

RUST-OLEUM[®]
INDUSTRIAL



9200 RUST-O-THANE[®]

Hardwearing 2 pack water based satin polyurethane

- Automotive level UV stability; does not yellow
- Water-based formula with low odour
- High abrasion resistance, extremely scratch resistant
- Smooth satin finish with excellent flow
- Can be used on floors, walls, stairs, wood and metal

footer_main_page_line_one

footer_main_page_line_two

9200 RUST-O-THANE®

POPIS PRODUKTU (DLHÝ)

Water-based satin gloss 2K polyurethane for a very durable and colourfast finish on metal or floors. Also ideal for doors, stairs, furniture, and as a topcoat for epoxy and acrylic systems.

ODPORÚČANÉ POUŽITIE

RUST-O-THANE 9200 is intended for application on interior and exterior substrates which are coated with RUST-OLEUM epoxy or acrylic coatings (e.g. RUST-OLEUM: 9100 and 5401, Pegasol or Pegalink). The application area consists of coated floors, coated walls and primed metal. Also ideal for use on stairs, doors, kitchen walls, floors and more. RUST-O-THANE 9200 assures appropriate protection against solvents, moderate alkalines, weak acids and chemical cleaning. Especially recommended where general urethane performance like excellent weather resistance (UV), easy cleaning and abrasion resistance is required.

TECHNICAL DATA

Hustota (g/cm ³):	1,23
Úroveň lesku:	Satin
Obsah pevných látok v objeme:	37%
Teplná odolnosť:	90°C (dry heat), above 65°C discoloration may occur
Pomer miešania:	Base : Activator = 5.66 : 1 by volume

DRY TIMES BY 20

Na dotyk suché:	2 hours
Suché na manipuláciu:	4 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	2 days
Život v hmci:	2 hours for a 5 litre mix at 20°C
Indukčný čas:	5 minutes

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

110 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm

TEORETICKÁ SPOTREBA

6,2 m²/l at 60 µm dry (depending on colour) for floors.
9,2 m²/l at 40 µm dry (depending on colour) for other applications.

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove grease, oil and all other surface contamination using alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand previous coatings that are in good condition to remove gloss and to roughen the surface slightly. Assure that the previous coating is compatible with the RUST-O-THANE 9200 by making a test application. Remove bad adhering coatings by scraping, wire brushing or sanding. (Spot)prime with commended Rust-Oleum or Mathys coatings. The surface must be clean and dry during application.

NÁVOD NA POUŽITIE

Add activator gradually to base material and mix with a mechanical mixing device. Do not dilute during the pot-life. Do not use after 2 hours. Do not store residue of mixed product in a closed can.

PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between 5°C and 35°C and relative humidity below 80 %. The substrate temperature must be at least 3°C above dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Use undiluted. Use natural bristles, long hair brushes.

APLIKÁCIA A RIEDENIE: VALEC

Use undiluted. Use medium nap (polyamide, 8-12 mm). Apply slowly in even strokes.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Use undiluted. Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch. Fluid pressure: 200 bar.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water and soap, before drying

POZNÁMKY

Max dry film thickness for floors: 75 µm dry, equals 200 µm wet. For walls: 60 µm dry, equals 160 µm wet.

For use on floors submitted to heavy abrasion, standard and medium colours are recommended. In case of deep and/or bright tones (red, yellow, orange, green, blue etc), it is advised to apply a clear topcoat.

The product is not recommended in case of stagnating water and/or immersion.

For dark or bright colors made from TR base, a minimum of two coats are necessary to achieve satisfactory opacity.

DATA SAFETY DATA

Úroveň VOC:	35 g/l
VOC readymix:	35 g/l
Kategória VOC:	A/j
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Base Minimum of 2 years and activator Minimum of 1 year from the date of production in unopened cans, if stored in dry, well-ventilated and frost-free areas, not in direct sunlight at temperatures between 5° and 35° C. Opened activator cans must be used within 1 week.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu