

RUST-OLEUM®
INDUSTRIAL



ASPHALT REPAIR



Immediately pot-hole repair

- Simple to use - no mixing required
- Repairs can be driven over immediately after application
- Ideal for repairs 10 mm – 70 mm
- Coverage approx. 0.5 m² per 25 kg at 24 mm thick
- Withstands heavy traffic

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ASPHALT REPAIR

OPIS

A durable bitumen-based patch repair for use on exterior pot-holed asphalt and concrete based on polished aggregate together with liquid binder based on bitumen plus resins and adhesives. Ideal for potholes in roads, car parks, paths and other bituminous and concrete surfaces.

ZALECANE UŻYCIE

Ideal for pot-holes in roadways, vehicle parks, loading docks, paths, airfields etc, on bituminous and concrete surfaces.

ZALECANA GRUBOŚĆ WARSTWY NA SUCHO

between 25 and 100 mm

ZUŻYCIE TEORETYCZNE

At a film thickness of 24 mm 25 kg will cover approximately 0.5m². The product can be applied up to 100mm film thickness.

ZUŻYCIE PRAKTYCZNE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRZYGOTOWANIE POWIERZCHNI

Remove all loose material and surface water, oil etc. Apply the primer with a brush on the prepared surface.

WARUNKI APLIKACJI

Temperature of air, substrate and coating material between 5 and 25°C. At lower temperatures the product will be tougher and is therefore more difficult to apply.

APLIKACJA I ROZCIEŃCZANIE: PACA/KIELNIA

Do not dilute the product.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu