

**RUST-OLEUM®**  
INDUSTRIAL



## ASPHALT RESTORER



# Freshes up discoloured asphalt

- Upgrades drab, grey, stained asphalt and tarmac
- Provides an 'as new' appearance
- Covers old line markings and repairs
- Avoids disruptive and costly re-surfacing

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# ASPHALT RESTORER

## DESCRIPTION

A one component high quality bitumen based coating with fillers and special flow additives. For refurbishing car parks, driveways and footpaths.

## RECOMMENDED\_USE

For refurbishing car parks, driveways and footpaths.

## DRY TIMES BY 20° C/RH 50%

group\_dry\_10\_touch: 30 minutes  
group\_dry\_30\_recoat: 2 - 5 hours  
group\_dry\_40\_full\_cure: 2 - 5 hours. Rain will delay curing by trapping solvents within the coating.

## GROUP\_COVERAGE\_10\_THEORETICAL

5 - 10 m<sup>2</sup> per 5 litres, depending on the surface.

## GROUP\_COVERAGE\_20\_PRACTICAL

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

## SURFACE\_PREPARATION

Surfaces should be dry and free of any loose material. Moss etc. should be removed by scraping and/or jet washing and the surface left to dry thoroughly.

## INSTRUCTIONS\_FOR\_USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION\_CONDITIONS

Do not apply during rainfall. Protect from rain for at least 30 minutes after application.

## GROUP\_APPL\_THINNING\_10\_BRUSH

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

## GROUP\_APPL\_THINNING\_20\_ROLLER

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

## REMARKS

This product is intended as a surface coating. It is not designed to strengthen or repair weak or damaged surfaces. This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.

## SAFETY DATA

group\_voc\_10\_level: 286 g/l  
group\_voc\_20\_readymix: 286 g/l  
group\_voc\_30\_category: A/i  
group\_voc\_40\_limit: 500 g/l  
safety\_remark\_PDS: Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF\_LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Дата на издаване: 10/03/2025

**Available colours & pack sizes:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Disclaimer:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)