

**RUST-OLEUM®**  
INDUSTRIAL



## B95SL FLEXIBLE EPOXY

# Flexible self-leveling epoxy



- Very flexible self-leveller, very wear- and impact-resistant
- High build and durable coating
- Good chemical and wear resistance
- Tintable in many colours
- Flexible, can also be used on asphalt

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# B95SL FLEXIBLE EPOXY

## ОПИСАНИЕ

Two-pack, flexible high-build self-leveling epoxy for floors. Excellent wear- and impact-resistance.

## ПРЕПОРЪЧАНА УПОТРЕБА

Flexible Epoxy B95SL should be used on cleaned, horizontal concrete floors, asphalt-concrete floors or other floors where flexibility is required. B95SL can be applied on cleaned, well adhering old epoxy floor coatings. The coating offers protection against abrasion and impact and can be applied in a dry film thickness of 150-200 µm (roller) to 2 mm (rake) in one coat. If good U.V. and chemical resistance is required, Polyurethane Topcoat 9600 or 9200 should be applied (except for 9211 or 9610 clear).

## ТЕХНИЧЕСКИ ДАННИ

Пълтност (г/см <sup>3</sup> ):	1,24
Гланцово ниво:	gloss
Съдържание на твърди частици в тегло:	96%
Съдържание на твърди вещества в обема:	96%
heat_resistance:	100°C (dry heat)
Степен на смесване:	1 : 1 (Volume)

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	16 hours (20°C), 24 hours (10°C)
Сух за употреба:	24 hours (20°C), 36 hours (10°C)
Готов за повторно нанасяне:	24 hours (20°C), 36 hours (10°C)
Напълно втвърден:	7 days (20°C), 14 days (10°C)
Живот в гърне:	45 minutes for a 20 litre. mix at 20°C
Време за въвеждане:	10 minutes for a 20 litre. mix at 20°C

## МОКЪР СЛОЙ

500 µm

## СУХ СЛОЙ

500 µm

## РАЗХОДНА НОРМА

2 m<sup>2</sup>/l

## КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

**General:** remove oil, grease and all other surface contaminations by alkaline or (high pressure) steam cleaning. The surface should be clean and dry during application.

Previously coated surfaces must be in sound condition and should be roughened in order to achieve optimal adhesion. A test-patch is recommended to check compatibility.

**Concrete:** new concrete should cure and dry for at least 30 days prior to the application of the product. Concrete curing compounds should be removed completely. All laitance, loose or unsound concrete should be removed by vacuum blasting or etching with Surf Etch 108. Irregularities should be levelled with Basecoat Rapid SL. Defects in the concrete should be repaired with Epoxy Repair mortar 5180 or 5412 directly after having primed with Impregnation Primer 5401 (wet into wet). For details see the Product Data Sheets. Very porous concrete should be primed with 5401.

**Asphalt-concrete:** New asphalt-concrete should cure and dry for at least 60 days prior to the application of the product. Defects in the surface should be repaired with the B95SL, with fire-dried quartz sand mixed into a ratio of approx. 1:1 in volume.

## НАЧИН НА УПОТРЕБА

Stir individual components thoroughly before mixing them together. Use the boxing method or use a low speed mixer.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## GROUP\_APPL\_THINNING\_50\_RAKE\_TROWEL

Pour the material onto the properly cleaned floor and spread it out evenly with a wide comb, rake or a spreader with triangular teeth. Then roll the surface with the de-aeration roller to release entrapped air and to promote the self-leveling effect.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use RUST-OLEUM Thinner 160.

## ЗАБЕЛЕЖКИ

Maximum dry film thickness per coat: 2 mm dry, equals 2 mm wet.

Check coverage regularly during application. Food should be stored separately or covered adequately during application of the B95 Self-Leveling epoxy. Some chemicals and solvents may cause discoloration and can affect the coating. The floor should be horizontal (max. 3 mm per metre incline, according to DIN 18 202, Table 3, Column 4) before applying the material in order to avoid excessive differences in dry film thickness.

Expansion joints should be filled with a flexible sealant.

B95 SL should always be top-coated with Polyurethane Topcoat 9200 or 9600.

## ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 31 g/l

Готов за употреба ЛОС

(VOC Readymix): 31 g/l

Категория ЛОС: A/j

Ограничение за ЛОС: 500 g/l

Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

## СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Дата на издаване:** 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоително в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Tor Coatings Ltd (Rust-Oleum Industrial)  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Rust-Oleum France S.A.S.  
36, av du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

N.V. Martin Mathys S.A.  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)