

**RUST-OLEUM®**  
— INDUSTRIAL —



## **BASECOAT RAPID SL 6570**

# **Rapid curing, self-leveling screed**

- Fast renovation of damaged or uneven floors
- Can be walked on after 4 hours
- Strong and durable material without portland cement
- Thickness of 5 – 30 mm thickness possible
- Almost no odour

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**

# BASECOAT RAPID SL 6570

## DESCRIPTION

Cost effective rapid curing, self-levelling screed to level out uneven floors.

## ODPORÚČANÉ POUŽITIE

Basecoat Rapid SL 6570 is designed to flatten out rough concrete floors. The product can be applied with a trowel, a rake or a special spreader with triangular teeth. The recommended layer thickness is 8 mm, but it is possible to apply the product at a thickness of 5 - 30 mm. Can be used with RUST-OLEUM topcoats to provide better aesthetics and improved wear and chemical resistance.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,7
Úroveň lesku:	Matt
Obsah pevných látok v hmotnosti:	83 % (mixed)
Obsah pevných látok v objeme:	75 % (mixed)
Tepelná odolnosť:	50°C (dry heat)
Pevnosť v tlaku:	35 MN/m <sup>2</sup>
Pevnosť v ohybe:	10 MN/m <sup>2</sup>

## DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	2-4 hours
Suché na manipuláciu:	4 hours
Suchý na opätovné natieranie:	1 day
Úplne vytvrdnuté:	7 days
Život v hmci:	15 minutes

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

5 - 30 mm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

4 - 26 mm

## TEORETICKÁ SPOTREBA

1,47 m<sup>2</sup> per 20 kg at 8 mm dry

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup>, free from laitance, dust and other contamination. The substrate should be dry to 75% RH (BS8204) and free from rising damp and ground water pressure.

## NÁVOD NA POUŽITIE

Add 3,6 – 3,8 litres of water per 20 kg bag and mix mechanically.

## PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between 5 and 25°C.

## APLIKÁCIA A RIEDENIE: HRABLAMI/HRABLIČKOU

Pour the material onto the properly cleaned floor and spread it out evenly with a rake or a trowel. Treat the surface directly after application with the de-aeration roller to release entrapped air and to promote the self-levelling effect.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Clean tools and spills with (hot) water before the product has started to cure.

## POZNÁMKY

Ensure the screed is not subject to draughts and strong sunlight during the first 24 hours of curing as this may lead to cracking and crazing.

- Fire Resistance BS 476-7 Spread of Flame: Class 1
- Impact Resistance BS 8204-1 Ca: A
- Abrasion Resistance BS 8204-2: Class AR2 / WS
- Adhesion to C30 concrete: > 1 N/mm<sup>2</sup> (28 days)
- Shrinkage: < 0.06%

## SAFETY DATA

Úroveň VOC:	0 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATEĽNOSŤ

Minimum of 6 months from date of production in unopened bags, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 10/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu