


**RUST-OLEUM®**  
— INDUSTRIAL —



## COMBICOLOR® AQUA



# One coat system for metal protection, direct to rust

- Primer and topcoat in one
- For application onto rust, bare metal
- High coverage: 10 m<sup>2</sup> per litre
- Sag resistant
- Usable down to 10°C

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# COMBICOLOR® AQUA

## BESKRIVELSE

RUST-OLEUM CombiColor Aqua coating is a primer and topcoat in one, based on a water-based acrylic resin with adhesion promoting properties and is fast drying. The product contains rust-inhibitive pigments and is lead, chromate and zinc-free.

## ANBEFALT BRUK

RUST-OLEUM CombiColor Aqua should be applied on bare, manually derusted or with CombiColor Aqua Primer primed steel. RUST-OLEUM CombiColor Aqua is intended for brush and roller application and can also be applied by air spray. RUST-OLEUM CombiColor Aqua offers corrosion protection in a light industrial environment. For metal structures in a more aggressive industrial environment, prior application of RUST-OLEUM CombiColor Aqua Primer is recommended.

## ANBEFALT SYSTEM

RUST-OLEUM CombiColor Aqua Primer / RUST-OLEUM CombiColor Aqua (Gloss or Satin)

## TEKNISKE DATA

Tetthet:	Gloss: 1.09 -1.19 - Satin: 1.20 - 1.30
Glansgrad:	Blank, Satinert
Glansgrad ved 60°:	Gloss: 85-95% - Satin: 35-45%
Tørrestoffinnhold i vekt:	Gloss: 45-55% - Satin: 50-60%
Tørrestoffinnhold i volum:	Gloss: 40-50% - Satin: 40-50%
Varmebestandig:	90°C (dry heat), at elevated temperatures discolouration may occur.

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	30 minutes (20°C)
Håndterbar:	90 minutes (20°C)
Overmalbar:	4hours (20°C)
Herdetid:	7 days

## ANBEFALT VÅTFILMYKKELSE

100 µm

## ANBEFALT TØRRFILMYKKELSE

Gloss: 40-50 µm - Satin: 40-50 µm

## TEORETISK FORBRUK

Gloss: 10 m<sup>2</sup>/L at 40-50 µm dry, depending on colour.  
Satin: 10 m<sup>2</sup>/L at 40-50 µm dry, depending on colour.

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

Remove oil, grease and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 3 (ISO 8501-1 : 1988), light blast cleaning or sanding. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with RUST-OLEUM CombiColor Aqua Primer.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 10° and 30°C and relative humidity below 80%. The substrate temperature must be at least 3°C above dew point.

## PÅFØRING & FORTYNNING: PENSEL

Thin only if necessary with maximum 3% volume water. Use a brush with synthetic bristles.

## PÅFØRING & FORTYNNING: RULLE

Thin only if necessary with maximum 3% volume water. Use short nap, polyamide 6-12mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Thin only if necessary with maximum 10% volume Water. Gravity cup and pressure cup. Tip size: 1.0 - 1.5 mm. Atomising pressure: 2 - 4 bar.

## RENGJØRING AV UTSTYR/SPILL

Use water.

## MERKNADER

Maximum dry film thickness per coat: 55 µm dry, equals 130 µm wet.

## SIKKERHETSDATA

VOC ferdigblandet:	5 g/l
VOC kategori:	A/i
VOC grense:	140 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)