

**RUST-OLEUM®**

INDUSTRIAL



## COMBICOLOR® ORIGINAL AEROSOLS

# One coat system for metal protection, direct to rust

- Primer and topcoat in one
- For application onto rust, bare metal
- Usable down to 5°C

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# COMBICOLOR® ORIGINAL AEROSOLS

## ОПИСАНИЕ

RUST-OLEUM® CombiColor Aerosols High Gloss 7300 are based on a urethane modified alkyd. Lead- and chromate-free - contains rust-inhibitive pigments for additional corrosion protection - good hiding properties - high gloss appearance.

## ПРЕПОРЪЧАНА УПОТРЕБА

RUST-OLEUM CombiColor Aerosols High Gloss 7300 can be applied directly on bare, manually derusted or with CombiPrimer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosols High Gloss 7300 are intended for small maintenance jobs or for touch-up. RUST-OLEUM CombiColor Aerosols High Gloss 7300 should be used in light industrial exposures, normal humidity and interior applications.

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух за употреба: 6 hours  
Готов за повторно нанасяне: After 2 hours  
Напълно втвърден: 7 days

## РАЗХОДНА НОРМА

2 - 3 m<sup>2</sup> per spray can (400 ml).

## КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiPrimer Tack Coat 3302.

## УСЛОВИЯ ЗА НАНАСЯНЕ

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

## GROUP\_APPL\_THINNING\_60\_AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## ЗАБЕЛЕЖКИ

Prevent application of too thick layers because this can cause problems with drying and sagging. CombiColor Aerosols can be applied on 7300 Metal (brush version) within 4 hours or after 72 hours.

## ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 535 - 540 g/l  
Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

## СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)