

**RUST-OLEUM®**  
INDUSTRIAL



## COMBIPRIMER® ADHESION PRIMER AEROSOL

**Makes the smoothest surface  
coatable!**

- Easy to apply
- Transparent blue finish
- Recoatable after just 30 minutes
- Very high coverage: 4,4 m<sup>2</sup>/can

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# COMBIPRIMER® ADHESION PRIMER AEROSOL

## DESCRIZIONE

RUST-OLEUM® CombiColor Aerosol Tack Coat 3302 is an adhesion coat based on a solvent containing acrylic.

## UTILIZZO CONSIGLIATO

RUST-OLEUM CombiColor Aerosol Tack Coat 3302 should be used on galvanized steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM CombiColor Aerosols 7300 Topcoats/ Hammered.  
RUST-OLEUM CombiColor Aerosol Tack Coat 3302 is intended for small maintenance jobs.  
RUST-OLEUM CombiColor Aerosol Tack Coat 3302 should be used in light industrial exposures, normal humidity and interior applications.

## DATI TECNICI

Densità: 0,87  
Residuo secco in volume: 7%

## TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto: Remains tacky  
Asciutto da maneggiare: Remains tacky  
Asciutto da rivestire: After 30 minutes but within 24 hours

## CONSUMO TEORICO

4.4 m<sup>2</sup> per spray can (400 ml)

## CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PREPARAZIONE DELLA SUPERFICIE

Remove dirt, grease, oil and all other surface contaminants by appropriate means or use RUST-OLEUM Alkaline Cleaner/Degreaser ND14. Remove previous coatings completely e.g. with RUST-OLEUM Paint Stripper DK20S. The surface must be clean and dry during application.

## ISTRUZIONI PER L'USO

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can at least 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a single, thin layer and avoid application of thick layers. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## CONDIZIONI DI APPLICAZIONE

For optimum results the relative humidity shall be below 85% and the temperature of the can above 0°C.

## APPLICAZIONE E DILUIZIONE: PENNELLO

Use natural bristles, longhair brushes.

## PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Use RUST-OLEUM Thinner 160.

## NOTE

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

## DATI RELATIVI ALLA SICUREZZA

Livello di COV:	730 g/l
Soluzione premiscelata COV:	741 g/l
Categoria COV:	A/h
Limite di COV:	750 g/l
grenelle:	aplus
Note riguardanti la sicurezza:	Consult Safety Data Sheet and Safety Information printed on the can.

## SCADENZA

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data del rilascio: 07/02/2025

**Colori e formati di confezione disponibili:** Si prega di consultare la pagina relativa al prodotto su [www.rust-oleum.eu](http://www.rust-oleum.eu) per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

**Dichiarazione di non responsabilità:** Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da [www.rust-oleum.eu](http://www.rust-oleum.eu) o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu