

RUST-OLEUM®
INDUSTRIAL



COMBIPRIMER® ADHESION PRIMER AEROSOL

**Makes the smoothest surface
coatable!**

- Easy to apply
- Transparent blue finish
- Recoatable after just 30 minutes
- Very high coverage: 4,4 m²/can

footer_main_page_line_one

footer_main_page_line_two

COMBIPRIMER® ADHESION PRIMER AEROSOL

POPIS PRODUKTU (DLHÝ)

RUST-OLEUM® CombiColor Aerosol Tack Coat 3302 is an adhesion coat based on a solvent containing acrylic.

ODPORÚČANÉ POUŽITIE

RUST-OLEUM CombiColor Aerosol Tack Coat 3302 should be used on galvanized steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM CombiColor Aerosols 7300 Topcoats/ Hammered.
RUST-OLEUM CombiColor Aerosol Tack Coat 3302 is intended for small maintenance jobs.
RUST-OLEUM CombiColor Aerosol Tack Coat 3302 should be used in light industrial exposures, normal humidity and interior applications.

TECHNICAL_DATA

Hustota (g/cm³): 0,87
Obsah pevných látok v objeme: 7%

DRY_TIMES_BY_20

Na dotyk suché: Remains tacky
Suché na manipuláciu: Remains tacky
Suchý na opätovné natieranie: After 30 minutes but within 24 hours

TEORETICKÁ SPOTREBA

4.4 m² per spray can (400 ml)

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove dirt, grease, oil and all other surface contaminants by appropriate means or use RUST-OLEUM Alkaline Cleaner/Degreaser ND14. Remove previous coatings completely e.g. with RUST-OLEUM Paint Stripper DK20S. The surface must be clean and dry during application.

NÁVOD NA POUŽITIE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can at least 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a single, thin layer and avoid application of thick layers. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

PODMIENKY APLIKÁCIE

For optimum results the relative humidity shall be below 85% and the temperature of the can above 0°C.

APLIKÁCIA A RIEDENIE: ŠTETEC

Use natural bristles, longhair brushes.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Use RUST-OLEUM Thinner 160.

POZNÁMKY

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

DATA SAFETY DATA

Úroveň VOC:	730 g/l
VOC readymix:	741 g/l
Kategória VOC:	A/h
Limit VOC:	750 g/l
Grenelle:	A+
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu