

RUST-OLEUM®
INDUSTRIAL



COATING PRT®

Flexible, long lasting finish for roofs or walls

- Flexible durable paint for renovation of roofs, ideal for making roofs white
- Resistant to UV, acid rain, heat, frost and pollution
- Ideal topcoat for DACFILL® or NOXYDE® to reduce dirt pickup
- Can be used in high humidity areas
- Can also be used on walls

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COATING PRT®

BESKRIVNING

Single pack high performance topcoat for walls and roofs, ideal for moist conditions and making roofs white. Also ideal to minimise dirt retention on DACFILL® or NOXYDE®.

REKOMMENDERAD ANVÄNDNING

- Coating of inner and outer walls that can be exposed to high humidity, f.i. bathrooms, kitchens, etc.
- Topcoat on Dacfill (improved resistance against stagnating water and less dirt retention) or on Noxyde (less dirt retention)

TEKNISK DATA

Densitet:	1,12
Glansnivå:	Satin
Torrsubstansvikt:	48%
Torrsubstansvolym:	42%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	3 hours
Hanteringstorr:	4 hours
Övermålningsbar:	24 hours
Fullt härdad:	24 hours

REKOMMENDERAD VÅFILMSTJOCKLEK

140 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

60 µm

TEORETISK FÖRBRUKNING

7 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

If the product is applied directly on bitumen felt, the consumption can be considerably higher. Account must be taken of 3.5 m² / l. Apply a test patch before starting the works in order to determine the actual practical consumption.

YTFÖRBEREDELSE

Clean the substrate. Allow to dry, any previous coatings must be completely dry.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Work in a dry and well-ventilated area.

APPLICERING OCH SPÄDNING: PENSEL

All types.

APPLICERING OCH SPÄDNING: ROLLER

Short nap-mohair roller.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Nozzle: 4/15 - Pressure: 100 bars.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Do not dilute.

RENGÖRING AV UTRUSTNING/SPILL

Thinner 22 or white spirit.

ANMÄRKNINGAR

Reversible paint system, this means that the product dissolves in its own solvent. Can be applied on new concrete.

SÄKERHETSDATA

VOC-nivå:	481 g/l
VOC färdigmix:	499 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
grenelle:	exterior
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu