


**RUST-OLEUM®**  
INDUSTRIAL



## DAC HYDRO ALU

# Solar reflective and durable roof coating

- Prevents strong warming up of the surface
- Lasting 400% elastic layer without seams or joints
- Decorative aluminium finish resist UV-radiation, temperature changes, water and pollution
- Waterproof guarantee when used as topcoat on Dacfill®
- Water-based formulation, low odour

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# DAC HYDRO ALU

## POPIS PRODUKTU (DLOUHÝ)

Waterborne, ready-to-use aluminum coating for decoration, heat reflection and lasting protection of metal and most bituminous roofs.

## DOPORUČENÉ POUŽITÍ

Decorative aluminium finish and durable protection of roofs with solar reflective characteristics. Builds an abrasion resistant rubberlike coat without joints or seams.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,05
Úroveň lesku:	Metallic
Obsah pevných látek v hmotnosti:	51%
Obsah pevných látek v objemu:	48%
Propustnost pro vodní páru:	$\mu = 1836$

## DRY TIMES BY 20

Dotykem suché:	4 hours
Suché na manipulaci:	6-7 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

1000 micron (cons.: 1 m<sup>2</sup>/l)

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

480 micron (cons.: 1 m<sup>2</sup>/l)

## TEORETICKÁ SPOTŘEBA

Waterproofing: 1 - 1,5 l/m<sup>2</sup> (depending on type of roof) as a second coat on Dacfill.  
Esthetical: 0,3 - 0,5 l/m<sup>2</sup>

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

The substrate must be clean, free from peeling, dust and dirt. Bridge cracks and fissures with Dacfill-mesh. Fill up joints with Elastofill. Very porous substrates have to be primed first with Primer 44HS. Dac-Hydro-Alu can be directly applied on metals (except new galvanised steel), roofing and most bituminous products (> 1 year). Dac-Hydro-Alu can be applied without any problem on most waterbased products like Dacfill and Noxyde. Do not apply directly on Fillcoat or Fillcoat Fibers. In this case it is necessary to apply first a coat of Dacfill. Dac-Hydro-Alu cannot be applied on flexible PVC, EPDM, tar or bituminous materials < 1 year, polyisobutylene and smooth bitumen-polymers. In case of stagnating water, Dac-Hydro-Alu must always be applied in combination with the Dacfill-mesh with a consumption of 2 l/m<sup>2</sup>.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Apply in drying conditions at minimum 5°C.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

All types, do not dilute

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Mohair roll with long hairs, do not dilute.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

In case of airless-application, the aluminium finish will not be uniform; an airless-roll application is ideal, although in case of an airless application, it is necessary to roll over the surface with a roller.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water

## DATA SAFETY DATA

Úroveň těkavých organických látek:	70 g/l
VOC readymix:	70 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	140 g/l
Grenelle:	Exterior
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu