

RUST-OLEUM®
INDUSTRIAL



DAC HYDRO PLUS

Decorative and protective roof tile paint

- Quick, easy to apply and affordable
- No need for a special primer on concrete
- Cost effective coverage: 10m²/L
- Lasting gloss and colour
- Rain-proof after just 2 hours

footer_main_page_line_one

footer_main_page_line_two

DAC HYDRO PLUS

POPIS PRODUKTU (DLHÝ)

Flexible and durable acrylic paint for renovation and protection of concrete roof tiles.

ODPORÚČANÉ POUŽITIE

Dac-Hydro-Plus renovates and protects in a durable way concrete and terracotta roof tiles.

TECHNICAL DATA

Hustota (g/cm ³):	1,16
Úroveň lesku:	Satin
Obsah pevných látok v hmotnosti:	40%
Obsah pevných látok v objeme:	30%

DRY TIMES BY 20

Na dotyk suché:	1 hour
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdené:	1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

1st coat: 110 µm (125 g/m²), 2nd coat: 85 µm (100 g/m²)

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

1st coat: 33 µm, 2nd coat: 26 µm

TEORETICKÁ SPOTREBA

10 m²/l per coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

After a good cleaning with pure water under high pressure (200 bars), all substrates have to be dry, clean, not chalking and normally absorbent (untreated roof tiles). Apply an anti fungicidal solution such as AMW fungicidal Wash for removal of moss, etc. Recommended primers for substrate:

Concrete: no primer required

Eternit/fibre cement: use Dac Hydro Pro

Slate tiles: Primer 44HS or Pegafix

Terracotta tiles, concrete tiles type Redland, fully weathered and/or very porous: Primer 44HS

Very dense substrates: Noxyde diluted with 25% volume water

It is recommended to always perform an adhesion test.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 8°C, relative humidity max. 80%. Do not apply in full sun.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted

APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Dilute with maximum 3% volume of water. Nozzle: 009 - 013 / Pressure: 140 – 180 bars.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

POZNÁMKY

Apply in 2 coats to avoid local gloss differences.

DATA SAFETY DATA

Úroveň VOC:	35 g/l
VOC readymix:	35 g/l
Kategória VOC:	A/i
Limit VOC:	140 g/l
Grenelle:	Exterior
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu