



# DACFILL® PU FIBRES

## OPIS

A high build, heavy duty, fibre loaded stripe coating, free from solvent odour that provides durable, long term protection for roofs. To be used on typical roof detail to soften angles/sharp edges etc. prior to over-coating with Dacfill® PU system.

## ZALECANE UŻYCIE

For application in conjunction with Dacfill PU roof waterproofing membrane systems. A high build, heavy duty coating, almost free from solvent odour that provides durable, long term protection for roofs. To be used in combination with regular Dacfill® PU system

## ZALECANY SYSTEM

Primers on metal

- Noxyde Plus
- Pegarust
- PVDF Primer
- 3388 Metal Primer

Primer for porous substrate

- 3377 Binder Sealer

Base coat

- Dacfill® PU Base coat avec Voile DacfillIV SDGF100
- Dacfill®PU Fibres

Topcoat

- Dacfill®PU Topcoat

## DANE TECHNICZNE

Gęstość:	1,45
Zawartość substancji stałych objętościowo:	87%

## CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk:	8 hours
Do użytku:	24 hours
Do przemalowania:	Min 24 hours, max 7 days
Czas przydatności do użycia:	-

## ZALECANA GRUBOŚĆ WARSTWY NA MOKRO

1,103 mm

## ZALECANA GRUBOŚĆ WARSTWY NA SUCHO

0,9 mm DFT/coat

## ZUŻYCIE TEORETYCZNE

1m<sup>2</sup> per litre per coat

## ZUŻYCIE PRAKTYCZNE

Dependent on surface profile, reinforcement where applicable etc.

## PRZYGOTOWANIE POWIERZCHNI

Inspect all surfaces to assess soundness of existing substrates or coatings. Where necessary prepare test areas. Roof surfaces must be clean, dry and free from all loose debris and be carried out before application of the coating. All areas of fungal growth, moss etc should be treated with AMW Fungicidal Wash and neutralised residues removed. Priming, where necessary should be carried out using suitable compatible materials. Contact Rust-O-Leum Technical Department for further advice.

## WSKAZÓWKI DOTYCZĄCE UŻYCIA

Prior to use, product should be carefully mixed until a full homogeneity is obtained

## WARUNKI APLIKACJI

Minimum application temperature: 3°C. Substrate temperature must be at least 3°C above dew point. Maximum relative humidity: 85%. Do not apply if rain is imminent.

## APLIKACJA I ROZCIEŃCZANIE: PĘDZEL

Do not thin

## APLIKACJA I ROZCIEŃCZANIE: WAŁEK

Do not thin

## APLIKACJA I ROZCIEŃCZANIE: NATRYSK BEZPOWIETRZNY

Not recommended

## APLIKACJA I ROZCIEŃCZANIE: NATRYSK POWIETRZNY

Not recommended

## CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Thinner 150

## UWAGI

Overcoating must be carried out within the timescale overleaf otherwise further preparation may be necessary.

For any information regarding options of guarantee with this system, please contact Technical Service.

This product does contain isocyanates. Users must follow mandatory training to comply with EU 2020/1149 Restriction 74.

## INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO:	< 175g/l
Kategoria LZO:	Cat A/i.
Limity LZO:	EU limit 500g/l

## OKRES TRWAŁOŚCI PRODUKTU

12 months from manufacturing date in unopened containers

Data wydania: 07/02/2025

**Dostępne kolory i opakowania:** Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej [www.rust-oleum.eu](http://www.rust-oleum.eu).

**Zrzeczenie się:** Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu