

RUST-OLEUM®
INDUSTRIAL



DACFILL® PU FIBRES

Fibre loaded stripe coating to soften angles

- very low solvent content
- soften angles on roof details
- smooth result
- Fibre loaded

footer_main_page_line_one

footer_main_page_line_two

DACFILL® PU FIBRES

POPIS PRODUKTU (DLHÝ)

A high build, heavy duty, fibre loaded stripe coating, free from solvent odour that provides durable, long term protection for roofs. To be used on typical roof detail to soften angles/sharp edges etc. prior to over-coating with Dacfill® PU system.

ODPORÚČANÉ POUŽITIE

For application in conjunction with Dacfill PU roof waterproofing membrane systems. A high build, heavy duty coating, almost free from solvent odour that provides durable, long term protection for roofs. To be used in combination with regular Dacfill® PU system

ODPORÚČANÝ SYSTÉM

Primers for on metal

- Noxyde Plus
- Pegarust
- PVDF Primer
- 3388 Metal Primer

Primer for porous substrate

- 3377 Binder Sealer

Base coat

- Dacfill® PU Base coat avec Voile DacfillIV SDGF100
- Dacfill®PU Fibres

Topcoat

- Dacfill®PU Topcoat

TECHNICAL_DATA

Hustota (g/cm³): 1,45

Obsah pevných látok v objeme: 87%

DRY_TIMES_BY_20

Na dotyk suché: 8 hours

Suché na manipuláciu: 24 hours

Suchý na opätovné natieranie: Min 24 hours, max 7 days

Život v hmci: -

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

1,103 mm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

0,9 mm DFT/coat

TEORETICKÁ SPOTREBA

1m² per litre per coat

PRAKTICKÁ VÝDATNOSŤ

Dependent on surface profile, reinforcement where applicable etc.

PRÍPRAVA POVRCHU

Inspect all surfaces to assess soundness of existing substrates or coatings. Where necessary prepare test areas. Roof surfaces must be clean, dry and free from all loose debris and be carried out before application of the coating. All areas of fungal growth, moss etc should be treated with AMW Fungicidal Wash and neutralised residues removed.

Priming, where necessary should be carried out using suitable compatible materials.

Contact Rust-O-Leum Technical Department for further advice.

NÁVOD NA POUŽITIE

Prior to use, product should be carefully mixed until a full homogeneity is obtained

PODMIENKY APLIKÁCIE

Minimum application temperature: 3°C. Substrate temperature must be at least 3°C above dew point. Maximum relative humidity: 85%.

Do not apply if rain is imminent.

APLIKÁCIA A RIEDENIE: ŠTETEC

Do not thin

APLIKÁCIA A RIEDENIE: VALEC

Do not thin

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not recommended

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended

ČISTENIE ZARIADENIA / POSTRIEKANIE

Thinner 150

POZNÁMKY

Overcoating must be carried out within the timescale overleaf otherwise further preparation may be necessary.

For any information regarding options of guarantee with this system, please contact Technical Service.

This product does contain isocyanates. Users must follow mandatory training to comply with EU 2020/1149 Restriction 74.

DATA_SAFETY_DATA

Úroveň VOC: < 175g/l

Kategória VOC: Cat A/i.

Limit VOC: EU limit 500g/l

SKLADOVATEĽNOSŤ

12 months from manufacturing date in unopened containers

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu