

RUST-OLEUM®
INDUSTRIAL



DACFILL® PU TOPCOAT



Seamless waterproofing membrane for roofs

- Easy to apply and detail
- Compatible with most existing roof membranes
- Permanent elastomeric and seamless
- Excellent resistance to ponded water
- Fibre reinforced for maximum film strength

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DACFILL® PU TOPCOAT

OPIS

Dacfill PU top coat is a low odour, cold applied single pack, ultra high solids moisture activated elastomeric urethane coating.

ZALECANE UŻYCIE

For application as the top coat in Dacfill PU roof waterproofing membrane systems. A high build, heavy duty coating, almost free from solvent odour that provides durable, long term protection for roofs. To be used as a fully reinforced weatherproofing system.

ZALECANY SYSTEM

3388 Metal Primer
3377 Binder Sealer
Dacfill PU Embedment coat
Dacfill Fleece
Dacfill PU Top coat
Dacfill PU Fibres

DANE TECHNICZNE

Gęstość: 1.45
Zawartość substancji stałych
objętościowo: 87%

CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk: 4 hours
Do użytku: 24 hours
Do przemalowania: min. 24 hours, max. 7 days

ZALECANA GRUBOŚĆ WARSTWY NA SUCHO

0.45-0.7 mm per coat (depending on the system)

ZUŻYCIE TEORETYCZNE

1-2m² per litre per coat

ZUŻYCIE PRAKTYCZNE

Dependent on surface profile, reinforcement where applicable etc.

PRZYGOTOWANIE POWIERZCHNI

Inspect all surfaces to assess soundness of existing substrates or coatings. Where necessary prepare test areas. Roof surfaces must be clean, dry and free from all loose debris and be carried out before application of the coating. All areas of fungal growth, moss etc should be treated with AMW Fungicidal Wash and neutralised residues removed. Apply over Dacfill Fleece reinforced Embedment Coat (where necessary). Priming, where necessary should be carried out using suitable compatible materials. Contact Rust-Oleum Technical Department for further advice.

WSKAZÓWKI DOTYCZĄCE UŻYCIA

Brush or roller. May be used as the carrier for Dacfill glass fibre reinforcement matting on localised repairs.

WARUNKI APLIKACJI

Do not apply if rain is imminent.

APLIKACJA I ROZCIEŃCZANIE: PĘDZEL

Do not thin

APLIKACJA I ROZCIEŃCZANIE: WAŁEK

Do not thin

CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Thinner 150

UWAGI

Overcoating must be carried out within the timescale overleaf otherwise further preparation may be necessary.

For any information regarding options of guarantee with this system, please contact Technical Service.

This product does contain isocyanates. Users must follow mandatory training to comply with EU 2020/1149 Restriction 74.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO: <175g/l
Kategoria LZO: Cat A/i
Limity LZO: EU limit 500 g/l

OKRES TRWAŁOŚCI PRODUKTU

12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu