

RUST-OLEUM®
INDUSTRIAL



DACFILL® PU TOPCOAT



Seamless waterproofing membrane for roofs

- Easy to apply and detail
- Compatible with most existing roof membranes
- Permanent elastomeric and seamless
- Excellent resistance to ponded water
- Fibre reinforced for maximum film strength

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DACFILL® PU TOPCOAT

BESKRIVNING

Dacfill PU top coat is a low odour, cold applied single pack, ultra high solids moisture activated elastomeric urethane coating.

REKOMMENDERAD ANVÄNDNING

For application as the top coat in Dacfill PU roof waterproofing membrane systems. A high build, heavy duty coating, almost free from solvent odour that provides durable, long term protection for roofs. To be used as a fully reinforced weatherproofing system.

REKOMMENDERAT SYSTEM

3388 Metal Primer
3377 Binder Sealer
Dacfill PU Embedment coat
Dacfill Fleece
Dacfill PU Top coat
Dacfill PU Fibres

TEKNISK DATA

Densitet: 1.45
Torrsubstansvolym: 87%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr: 4 hours
Hanteringstorr: 24 hours
Övermålningsbar: min. 24 hours, max. 7 days

REKOMMENDERAD TORRFILMSTJOCKLEK

0.45-0.7 mm per coat (depending on the system)

TEORETISK FÖRBRUKNING

1-2m² per litre per coat

PRAKTISK FÖRBRUKNING

Dependent on surface profile, reinforcement where applicable etc.

YTFÖRBEREDELSE

Inspect all surfaces to assess soundness of existing substrates or coatings. Where necessary prepare test areas. Roof surfaces must be clean, dry and free from all loose debris and be carried out before application of the coating. All areas of fungal growth, moss etc should be treated with AMW Fungicidal Wash and neutralised residues removed. Apply over Dacfill Fleece reinforced Embedment Coat (where necessary). Priming, where necessary should be carried out using suitable compatible materials. Contact Rust-Oleum Technical Department for further advice.

BRUKSANVISNING

Brush or roller. May be used as the carrier for Dacfill glass fibre reinforcement matting on localised repairs.

APPLICERINGSFÖRHÅLLANDEN

Do not apply if rain is imminent.

APPLICERING OCH SPÄDNING: PENSEL

Do not thin

APPLICERING OCH SPÄDNING: ROLLER

Do not thin

RENGÖRING AV UTRUSTNING/SPILL

Thinner 150

ANMÄRKNINGAR

Overcoating must be carried out within the timescale overleaf otherwise further preparation may be necessary.

For any information regarding options of guarantee with this system, please contact Technical Service.

This product does contain isocyanates. Users must follow mandatory training to comply with EU 2020/1149 Restriction 74.

SÄKERHETSDATA

VOC-nivå: <175g/l
VOC-kategori: Cat A/i
VOC-gräns: EU limit 500 g/l

HÅLLBARHET

12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu