

RUST-OLEUM®
INDUSTRIAL



EPOXYSHIELD® CLEANER/DEGREASER



A concentrated cleaner and degreaser for floors.

- Removes grease, oil and other contaminations
- Virtually odour free
- Non-flammable
- 6-8 m²/l coverage

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® CLEANER/DEGREASER

BESKRIVELSE

Cleaner/Degreaser for floors is a concentrated, alkaline, non-flammable, virtually odour-free cleaning/degreasing solution.

ANBEFALET BRUG

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors should be used to remove grease, oil, proteins, dirt and many other surface contaminants from coated, mineral and steel substrates. RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors should be applied with an artificial sponge, cloth or stiff nylon brush or broom. RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors can also be used as an additive for high-pressure (steam) cleaning.

TEORETISK FORBRUG

6 - 8 m²/l

PRAKTISK FORBRUG

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

BRUGSANVISNING

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors can be applied with a sponge, cloth, brush, and broom or cleaning machine. When used in combination with a cleaning machine dilute with 50% cold water. After use rinse with plenty of fresh water. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

ANVENDELSBETINGELSER

Temperature of air, substrate and material between 5 and 35°C.

BEMÆRKNINGER

Always rinse the surface after cleaning.

SIKKERHEDSDATA

VOC-niveau: 9 g/l
Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 02/01/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu