

RUST-OLEUM®
INDUSTRIAL



EPOXYSHIELD® CLEANER/DEGREASER



A concentrated cleaner and degreaser for floors.

- Removes grease, oil and other contaminations
- Virtually odour free
- Non-flammable
- 6-8 m²/l coverage

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® CLEANER/DEGREASER

OPIS

Cleaner/Degreaser for floors is a concentrated, alkaline, non-flammable, virtually odour-free cleaning/degreasing solution.

ZAŁECANE UŻYCIĘ

RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors should be used to remove grease, oil, proteins, dirt and many other surface contaminants from coated, mineral and steel substrates. RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors should be applied with an artificial sponge, cloth or stiff nylon brush or broom. RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors can also be used as an additive for high-pressure (steam) cleaning.

ZUŻYCIĘ TEORETYCZNE

6 - 8 m²/l

ZUŻYCIĘ PRAKTYCZNE

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

WSKAZÓWKI DOTYCZĄCE UŻYCIA

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. RUST-OLEUM® 2901 - EPOXYSHIELD® Cleaner/Degreaser for floors can be applied with a sponge, cloth, brush, and broom or cleaning machine. When used in combination with a cleaning machine dilute with 50% cold water. After use rinse with plenty of fresh water. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

WARUNKI APLIKACJI

Temperature of air, substrate and material between 5 and 35°C.

UWAGI

Always rinse the surface after cleaning.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO: 9 g/l
Uwagi dotyczące bezpieczeństwa: Consult Safety Data Sheet and Safety Information printed on the can.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu