

RUST-OLEUM
INDUSTRIAL



EPOXYSHIELD® GARAGE FLOOR COATING



Complete kit, ultimate adhesion and durability

- 2-part water based epoxy
- Complete kit including instructions
- Resists gasoline, antifreeze, motor oil, salt and hot tire pick-up

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® GARAGE FLOOR COATING

DESCRIZIONE

Epoxyshield® is a user friendly and easy to apply water-based epoxy garage floor coating with an ultimate adhesion and durability. The product has an excellent wear, impact and abrasion resistance like heavy foot and vehicle traffic. Resists chemicals.

UTILIZZO CONSIGLIATO

Apply on concrete floors, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a curing compound, which will prevent a good adhesion. Epoxyshield® can also be applied on old good adhering coatings.

DATI TECNICI

Densità:	1,27
Livello di lucentezza:	Satinato
Residuo secco in volume:	63.6%
Rapporto di miscelazione:	Base : Activator = 3 : 1 (volume)

TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto da maneggiare:	16 hours (suitable for light foot traffic)
Asciutto da rivestire:	48 hours (suitable for normal foot traffic and heavy items)
Completamente indurito:	7 days (suitable for vehicle traffic)
Durata del contenitore:	2 hours (15°C), 1½ hours (20°C), 1 hours (25°C)
Tempo di induzione:	Brush: 30 minutes (15°C), 10 minutes (20°C), Direct (25°C). Roller: 45 minutes (15°C), 15 minutes (20°C), 5 - 15 minutes (25°C)

CONSUMO TEORICO

Each Epoxyshield® kit contains enough product to cover approximately 25 m² of smooth, bare concrete (a normal 1 car concrete garage floor). Very rough or porous concrete may require more material. Expect coverage of 12-20 m² on those surfaces

PREPARAZIONE DELLA SUPERFICIE

Remove any oil or grease spots on the floor. Use a scrub brush and a cleaner/degreaser or use a solvent such as mineral spirits. Scrub the spot thoroughly and wipe up excess cleaner with rags or paper towels to keep contaminants from spreading. Rinse thoroughly with fresh water. Repeat as necessary to completely clean. Mix all concentrated cleaner from the kit with approximately 7½-litre water. Mix until dissolved (the cleaning solution contains citric acid). Pre-wet the floor using a hose. Remove pooled water with a squeegee or broom to avoid leaving puddles. Spread the cleaner mixture over a 3x3-m² section of the floor using a watering can. Scrub vigorously with a stiff bristle brush to loosen dust and dirt. While working, keep the entire section wet until the entire section has been cleaned and rinsed. Rinse each section thoroughly before starting the next section. For best results, use a foam squeegee to remove the rinse water from the surface and to move dirt and contaminants out of the garage. Once all sections are completed, rinse and squeegee the entire garage floor to remove any cleaner that has tracked on previously cleaned areas. A wet/dry vacuum cleaner can also be used to eliminate excess water, dirt and contaminants. Do not leave pooled water on the floor. The cleaner will not discolour driveways or harm grass or plants if rinsed thoroughly. Allow the floor to dry completely. Wipe your fingers over the clean, dry floor. If you see any dust or powder on your fingers, repeat the rinsing and scrubbing until the floor is clean.

ISTRUZIONI PER L'USO

Do not mix Paint Chips with Epoxyshield®. Pour the contents of A into B and stir thoroughly for at least 3 minutes. Allow mixed product to stand (see table) before rolling the coating on to the surface. Do not leave container in direct sunlight. Mix again before applying. The product must be used within 1 to 2 hours of initial mixing (pot life, see table). This time decreases at higher temperatures.

CONDIZIONI DI APPLICAZIONE

Apply when air (ambient) temperature is 15-35°C and relative humidity is below 80%. Concrete floors take a long time to warm up; make sure the previous day has also been at least 15°C prior to painting. Minimum floor temperature for painting is 13°C. Painting in midafternoon ensures the best cure.

APPLICAZIONE E DILUIZIONE: RULLO

After the full 60 minutes use a paint roller (20 cm) to apply an even coat of Epoxyshield® onto the surface. Apply in sections of 1,5 x 1,5 m so that paint chips can easily be scattered on the freshly coated surface. Maintain a wet edge to prevent lap marks and gloss differences. Sprinkle the decorative paint chips onto the wet film (note: this step may be skipped if chips are not desired. This will not affect the performance of the coating). Immediately continue to coat the next section (note: fresh paint can be applied over the loose chips that lay outside the previously painted area). This product must be used within 3 hours of initial mixing (pot life).

PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Wash all tools and equipment immediately with warm water and mild detergent. Allow any unused product to harden in the container and discard according to local regulations.

NOTE

It is not recommended to apply Epoxyshield on floors treated with a levelling mortar or on anhydride floors. Since the application time is only 1 - 2 hours (depending on temperature) it is advisable to apply the product with 2 persons. Have 1 person begin trimming edges and have another person begin rolling out the floor as specified.

DATI RELATIVI ALLA SICUREZZA

Livello di COV:	53 g/l
Soluzione premiscelata COV:	53 g/l
Categoria COV:	A/j
Limite di COV:	140 g/l
Note riguardanti la sicurezza:	Avoid contact with skin and eyes. For skin contact, wash affected area with soap and water and rinse well. First aid: in case of contact with eyes, flush with cold water for 15 minutes. If swallowed, do not induce vomiting. Drink 1-2 glasses of water or milk. Contact a physician immediately. Keep out of reach of children. Do not take internally. Consult for further information the Safety Data Sheet and the Safety Information printed on the can.

SCADENZA

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.

Data del rilascio: 07/02/2025

Colori e formati di confezione disponibili: Si prega di consultare la pagina relativa al prodotto su www.rust-oleum.eu per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

Dichiarazione di non responsabilità: Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da www.rust-oleum.eu o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu