

**RUST-OLEUM®**  
INDUSTRIAL



## EPOXYSHIELD® ULTRA



# Single pack water based quick drying floor coating

- For light to medium traffic
- Easy to apply
- Touch dry after just 2 hours
- Satin matt finish
- Good resistance to car tyres and various chemicals

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# EPOXYSHIELD® ULTRA

## POPIS PRODUKTU (DLOUHÝ)

A quick-drying single pack water-based floor coating (epoxy-modified acrylic) for light to medium duty (normal foot traffic/limited vehicular traffic). Good resistance to diesel, motor oil, coolant fluid, various household chemicals and most types of tyre.

## DOPORUČENÉ POUŽITÍ

EpoxyShield® 5200 ULTRA can be applied on concrete floors which are completely clean, dry and treated with EpoxyShield® Sealer 5220. Do not apply to smooth and completely sealed concrete or concrete containing a curing compound. Such substrates will prevent a good adhesion. EpoxyShield® 5200 ULTRA can also be applied on old good adhering coatings.

## TECHNICAL\_DATA

|                                  |             |
|----------------------------------|-------------|
| Hustota (g/cm <sup>3</sup> ):    | 1,16 - 1,21 |
| Úroveň lesku:                    | Satin       |
| Obsah pevných látek v hmotnosti: | 48-52%      |
| Obsah pevných látek v objemu:    | 38% - 42%   |

## DRY\_TIMES\_BY\_20

|                      |   |
|----------------------|---|
| Dotykem suché:       | 2 hours (20°C), 4 hours (10°C), 1½ hours (30°C) |
| Suché na manipulaci: | 6 hours (20°C), 8 hours (10°C), 4 hours (30°C)  |
| Suchý nátěr:         | 6 hours (20°C), 8 hours (10°C), 4 hours (30°C)  |
| Plně vytvrzené:      | 1 week (20°C), 1 week (10°C), 1 week (30°C)     |

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

40 µm

## TEORETICKÁ SPOTŘEBA

Approx. 9 m<sup>2</sup>/l at 40 µm dry

## PRAKTICKÁ SPOTŘEBA

Approx. 9 +/- 2 m<sup>2</sup>/l. Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove oil, grease and all other contaminants with EpoxyShield® Cleaner/Degreaser 2901 in combination with high pressure cleaning. Allow new concrete to set for at least 30 days before applying a coating. Remove laitance, loose and damaged concrete by sandblasting or etching with RUSTOLEUM Surfa-Etch 108. Repair all holes and cracks with EpoxyShield® concrete repair products. Always pre-treat absorbent, porous surfaces with EpoxyShield® Sealer 5220. Roughen or blast well-sealed and smooth concrete and treat with EpoxyShield® Sealer 5220 or apply a coat RUST-OLEUM 3333 Super Adhesive. Roughen still-intact floor coatings to ensure good adherence. Remove poorly adhering old coatings with wire brush and sandpaper. During application the surface must be clean and dry.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Temperature of air, substrate and coating material between 10 and 35°C. Relative humidity below 85%. The temperature of the surface must be at least 3°C above the dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Product is ready for use, dilution is not necessary.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Product is ready for use, dilution is not necessary. Use a nylon paint roller (ca. 12 mm). In case of roller application it can be necessary to apply 2 coats in order to achieve the prescribed film thickness.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Direct after application with water and soap.

## POZNÁMKY

In order to improve abrasion resistance the product can be mixed with Rust-Oleum Ultra Wear 400. One packaging (750 gram) is sufficient for 5-litre product. The mixture must be stirred regularly in order to prevent settling on the bottom of the can. In case of petrol spilling/leakage do not wipe the floor dry but let evaporate. The coating will restore itself. It is advisable to wait for at least 1 week after application before parking a vehicle. Not recommended for floors submitted to prolonged contact with water.

## DATA SAFETY DATA

|                                    |  |
|------------------------------------|--|
| Úroveň těkavých organických látek: | 72 g/l   |
| VOC readymix:                      | 72 g/l   |
| Kategorie VOC:                     | A/i  |
| Limitní hodnota VOC:               | 140 g/l  |
| Poznámky k bezpečnosti:            | Consult Safety Data Sheet and Safety Information printed on the can. |

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu