

RUST-OLEUM®
INDUSTRIAL



EPOXYSHIELD® ULTRA



Single pack water based quick drying floor coating

- For light to medium traffic
- Easy to apply
- Touch dry after just 2 hours
- Satin matt finish
- Good resistance to car tyres and various chemicals

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® ULTRA

BESKRIVELSE

A quick-drying single pack water-based floor coating (epoxy-modified acrylic) for light to medium duty (normal foot traffic/limited vehicular traffic). Good resistance to diesel, motor oil, coolant fluid, various household chemicals and most types of tyre.

ANBEFALT BRUK

EpoxyShield® 5200 ULTRA can be applied on concrete floors which are completely clean, dry and treated with EpoxyShield® Sealer 5220. Do not apply to smooth and completely sealed concrete or concrete containing a curing compound. Such substrates will prevent a good adhesion. EpoxyShield® 5200 ULTRA can also be applied on old good adhering coatings.

TEKNISKE DATA

Tetthet:	1,16 - 1,21
Glansgrad:	Satinert
Tørrstoffinnhold i vekt:	48-52%
Tørrstoffinnhold i volum:	38% - 42%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	2 hours (20°C), 4 hours (10°C), 1½ hours (30°C)
Håndterbar:	6 hours (20°C), 8 hours (10°C), 4 hours (30°C)
Overmalbar:	6 hours (20°C), 8 hours (10°C), 4 hours (30°C)
Herdetid:	1 week (20°C), 1 week (10°C), 1 week (30°C)

ANBEFALT VÅTFILMTYKKELSE

100 µm

ANBEFALT TØRRFILMTYKKELSE

40 µm

TEORETISK FORBRUK

Approx. 9 m²/l at 40 µm dry

PRAKTISK FORBRUK

Approx. 9 +/- 2 m²/l. Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove oil, grease and all other contaminants with EpoxyShield® Cleaner/Degreaser 2901 in combination with high pressure cleaning. Allow new concrete to set for at least 30 days before applying a coating. Remove laitance, loose and damaged concrete by sandblasting or etching with RUSTOLEUM Surfa-Etch 108. Repair all holes and cracks with EpoxyShield® concrete repair products. Always pre-treat absorbent, porous surfaces with EpoxyShield® Sealer 5220. Roughen or blast well-sealed and smooth concrete and treat with Epoxyshield® Sealer 5220 or apply a coat RUST-OLEUM 3333 Super Adhesive. Roughen still-intact floor coatings to ensure good adherence. Remove poorly adhering old coatings with wire brush and sandpaper. During application the surface must be clean and dry.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 10 and 35°C. Relative humidity below 85%. The temperature of the surface must be at least 3°C above the dew point.

PÅFØRING & FORTYNNING: PENSEL

Product is ready for use, dilution is not necessary.

PÅFØRING & FORTYNNING: RULLE

Product is ready for use, dilution is not necessary. Use a nylon paint roller (ca. 12 mm). In case of roller application it can be necessary to apply 2 coats in order to achieve the prescribed film thickness.

RENGJØRING AV UTSTYR/SPILL

Direct after application with water and soap.

MERKNADER

In order to improve abrasion resistance the product can be mixed with Rust-Oleum Ultra Wear 400. One packaging (750 gram) is sufficient for 5-litre product. The mixture must be stirred regularly in order to prevent settling on the bottom of the can. In case of petrol spilling/leakage do not wipe the floor dry but let evaporate. The coating will restore itself. It is advisable to wait for at least 1 week after application before parking a vehicle. Not recommended for floors submitted to prolonged contact with water.

SIKKERHETSDATA

VOC nivå:	72 g/l
VOC ferdigblandet:	72 g/l
VOC kategori:	A/i
VOC grense:	140 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu