

RUST-OLEUM®
INDUSTRIAL



9740 FAST BALCONY SYSTEM TOPCOAT

Sealercoat based on a polyaspartic resin system



- Low odour formula
- Walkable after 60-90 mins
- 1-2 coat fully reinforced waterproofing membrane
- Easy to apply and detail
- Low textured, slip resistant finish

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

9740 FAST BALCONY SYSTEM TOPCOAT

BESKRIVELSE

A low solvent odour, flexible top coat for use within the Rust-Oleum Fast Balcony System to encapsulate anti-slip aggregates and provide a durable, full gloss finish.

ANBEFALT BRUK

The topcoat of the Fast Balcony System system is specifically intended for use on medium to high wear areas on communal balconies and walkways

ANBEFALT SYSTEM

Fast Balcony System Grit Coat in combination with Dacfill Fleece
Aluminum Oxide Grits
Fast Balcony System Top Coat

TEKNISKE DATA

Tetthet: 1,1
Glansgrad ved 60°: Gloss
Glansgrad ved 85°: Gloss
Tørrestoffinnhold i volum: 85%
Blandeforhold: Stir base to even consistency then add one complete unit of activator. Mix well to uniform blend, ensuring base material is worked away from sides and bottom of container.

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr: 1 hour
Håndterbar: 1,5 hour
Overmalbar: min 1,5 hr, max 3 days
Brukstid: 15 minutes at 20°C

ANBEFALT VÅTFILMTYKKELSE

170 microns

TEORETISK FORBRUK

4-5m²/liter achieves 170-210 microns dry

PRAKTISK FORBRUK

Typically 4-6m²/liter. Coverage rate may vary depending on size, type and spreading rate of aluminium oxide grits.

KLARGJØRING AV OVERFLATE

Apply the aggregate in the wet paint film

BRUKSANVISNING

Temperatures above 25°C and very high humidity will reduce pot life. Application at very low temperatures will significantly retard cure. Do not apply when rain is imminent.

PÅFØRING & FORTYNNING: PENSEL

Do not thin

PÅFØRING & FORTYNNING: RULLE

Apply one coat by roller to give an even spread, ensuring good cover on entire surface. Apply mixed material as soon as possible to maintain workability. Do not thin.

RENGJØRING AV UTSTYR/SPILL

Thinner 150

MERKNADER

Do not apply to inadequately prepared or unsound surfaces. This product should only be applied by Rust-Oleum approved contractors (further details on request). Substrates must be dry during application otherwise curing defects will occur.

SIKKERHETSDATA

VOC nivå: <200 g/l
VOC kategori: cat A/j
VOC grense: 500 g/l

HOLDBARHET

12 months from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5°C and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu