

**RUST-OLEUM®**  
INDUSTRIAL



## 9740 FAST BALCONY SYSTEM TOPCOAT

# Sealercoat based on a polyaspartic resin system



- Low odour formula
- Walkable after 60-90 mins
- 1-2 coat fully reinforced waterproofing membrane
- Easy to apply and detail
- Low textured, slip resistant finish

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# 9740 FAST BALCONY SYSTEM TOPCOAT

## POPIS PRODUKTU (DLHÝ)

A low solvent odour, flexible top coat for use within the Rust-Oleum Fast Balcony System to encapsulate anti-slip aggregates and provide a durable, full gloss finish.

## ODPORÚČANÉ POUŽITIE

The topcoat of the Fast Balcony System system is specifically intended for use on medium to high wear areas on communal balconies and walkways

## ODPORÚČANÝ SYSTÉM

Fast Balcony System Grit Coat in combination with Dacfill Fleece  
Aluminum Oxide Grits  
Fast Balcony System Top Coat

## TECHNICAL\_DATA

Hustota (g/cm<sup>3</sup>): 1,1  
Úroveň lesku pri 60°: Gloss  
Úroveň lesku pri 85°: Gloss  
Obsah pevných látok v objeme: 85%  
Pomer miešania: Stir base to even consistency then add one complete unit of activator. Mix well to uniform blend, ensuring base material is worked away from sides and bottom of container.

## DRY\_TIMES\_BY\_20

Na dotyk suché: 1 hour  
Suché na manipuláciu: 1,5 hour  
Suchý na opätovné natieranie: min 1,5 hr, max 3 days  
Život v hrnci: 15 minutes at 20°C

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

170 microns

## TEORETICKÁ SPOTREBA

4-5m<sup>2</sup>/liter achieves 170-210 microns dry

## PRAKTICKÁ VÝDATNOSŤ

Typically 4-6m<sup>2</sup>/liter. Coverage rate may vary depending on size, type and spreading rate of aluminium oxide grits.

## PRÍPRAVA POVRCHU

Apply the aggregate in the wet paint film

## NÁVOD NA POUŽITIE

Temperatures above 25°C and very high humidity will reduce pot life. Application at very low temperatures will significantly retard cure. Do not apply when rain is imminent.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Do not thin

## APLIKÁCIA A RIEDENIE: VALEC

Apply one coat by roller to give an even spread, ensuring good cover on entire surface. Apply mixed material as soon as possible to maintain workability. Do not thin.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Thinner 150

## POZNÁMKY

Do not apply to inadequately prepared or unsound surfaces. This product should only be applied by Rust-Oleum approved contractors (further details on request). Substrates must be dry during application otherwise curing defects will occur.

## DATA SAFETY DATA

Úroveň VOC: <200 g/l  
Kategória VOC: cat A/j  
Limit VOC: 500 g/l

## SKLADOVATEĽNOSŤ

12 months from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5°C and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu