

RUST-OLEUM®
INDUSTRIAL



FILLCOAT® FIBRES WATERPROOFING

Stops leaks instantly, crack-bridging

- Repairs holes and cracks up to 2mm instantly
- Excellent adhesion to various substrates
- Can be applied in all weather conditions
- Direct repair of gutters, roofs, chimney stacks, pipes and more
- Bitumen-free formula



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

FILLCOAT® FIBRES WATERPROOFING

BESKRIVNING

Instantly waterproof elastic paint with crack-bridging fibres for roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc. The product has better UV resistance and improved hydrophobic properties.

REKOMMENDERAD ANVÄNDNING

Waterproof finish of roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc. Product is recoatable with Dacfill, Coating PRT or Dacfill HZ.

TEKNISK DATA

Densitet:	1,01
Glansnivå:	Satin
Torrsubstansvikt:	52%
Torrsubstansvolym:	43%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	4 h
Övermålningsbar:	3 - 14 days with the same product. 6 weeks with a paint
Fullt härdad:	3 weeks

REKOMMENDERAD VÅTFILMSTJOCKLEK

1000 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

430 µm

TEORETISK FÖRBRUKNING

1 m²/L at 430 µm dry

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Remove dust, mud, grease, moss and withered leaves carefully. The spots to be repaired are cleaned with a hard broom and sponged. After cleaning, Fillcoat Fibres can be applied directly on bituminous substrates, hard PVC, polyester, zinc, aluminium, glass, tiles, etc. Porous materials (concrete, stone, wood) must first be dried and pre-treated with a coat of Primer 44HS. In case of repeatedly repaired spots, important or active cracks, apply Fillcoat Fibres crosswise over the cracks or fissures.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Can be applied during all weather conditions, except for snow.

APPLICERING OCH SPÄDNING: PENSEL

Do not dilute.

RENGÖRING AV UTRUSTNING/SPILL

Thinner 22 or white spirit.

ANMÄRKNINGAR

Never apply Fillcoat Fibres to polystyrene insulation or onto new concrete (concrete should be at least 2 year old). Do not apply Fillcoat Fibres as priming coat under Dac Hydro Alu.

SÄKERHETSDATA

VOC-nivå:	485 g/l
VOC färdigmix:	485 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
grenelle:	exterior
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu