

RUST-OLEUM®
INDUSTRIAL



FK111 CLEANER/DEGREASER

Alkaline cleaner in gel form for walls

- High-viscosity formulation is ideal for use on walls, does not run off the wall
- Removes grease, oil, proteins, dirt and many other contaminants
- Ready-use mixture, can be diluted for light pollution
- Neutralizes acids and acidic salts
- Non-flammable, virtually odour-free

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

FK111 CLEANER/DEGREASER

DESCRIPTION

Concentrated, alkaline, non-flammable, virtually odour free, gel-like cleaning and degreasing solution for vertical substrates like walls.

DOPORUČENÉ POUŽITÍ

Used to remove oil, grease, proteins and many other surface contaminations; it neutralizes acids and acidic salts. FK 111 Cleaning Solution should be applied with a stiff nylon brush or broom.

TEORETICKÁ SPOTŘEBA

6 - 8 m²/l

PRAKTICKÁ SPOTŘEBA

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

NÁVOD K POUŽITÍ

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. Scrub FK111 into the surface using a stiff (nylon) bristle brush. Allow to stand for 5 to 10 minutes and clean thoroughly by flushing with plenty of fresh water. FK111 should normally be applied as delivered. However, it can be diluted with fresh water up to 1 : 2 parts, when applied on surfaces which are slightly contaminated. Can also be used as an additive for (high-pressure) steam cleaning, in concentrations from 5% up to 25% for severely contaminated surfaces, followed by (steam) cleaning or rinsing with fresh water. After cleaning, remove any remaining water and allow to dry completely, as moisture left on the surface or entrapped into pores may cause failure of the coating system. Do not allow to dry before rinsing! Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

PODMÍNKY POUŽITÍ

Temperature of air, substrate and material between 5 and 35°C.

SAFETY DATA

Úroveň těkavých organických

látek: 0 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

PH

11

DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 20/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu