

RUST-OLEUM®
INDUSTRIAL



3202 GALVINOX®

Super adhesion primer

- Adheres to all smooth metal, like galvanized and stainless steel, aluminium, plastics etc.
- Recoatable after just 30 minutes
- Very high coverage: 50 m²/l
- Also for use on glass, plastics and porcelain
- Single pack product

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3202 GALVINOLEUM®

BESKRIVNING

Single pack super adhesion primer for galvanised steel, plastic or other smooth surfaces.

REKOMMENDERAD ANVÄNDNING

Galvinoleum 3202 should be used on galvanised steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces. Only intended for brush application. Can be recoated with Alkythane® 7500, improving the adhesion on very smooth and non-porous surfaces.

TEKNISK DATA

Densitet:	0,92
Glansnivå:	Glans
Korrosionsklass:	C1/C2 låg korrosion
Torrsubstansvikt:	20%
Torrsubstansvolym:	16%
Värmebeständighet:	100 °C (dry heat)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	Remains tacky
Hanteringstorr:	Remains tacky
Övermålningsbar:	After 30 minutes but within 24 hours
Fullt härdad:	24 hours

REKOMMENDERAD VÅTFILMSTJOCKLEK

25-30 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

4-5 µm

TEORETISK FÖRBRUKNING

35 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove previous coatings completely. Remove salts, 'white rust', etc., by washing with Surfa-Etch 108 Etching Solution. The surface must be clean and dry during application.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

APPLICERING OCH SPÅDNING: PENSEL

Use natural bristles, long hair brushes.

APPLICERING OCH SPÅDNING: ROLLER

Not recommended.

RENGÖRING AV UTRUSTNING/SPILL

Use RUST-OLEUM Thinner 160 or aromatic hydrocarbons.

ANMÄRKNINGAR

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

SÄKERHETSDATA

VOC-nivå:	745 g/l
VOC färdigmix:	745 g/l
VOC-kategori:	A/h
VOC-gräns:	750 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu