

RUST-OLEUM®
INDUSTRIAL



GROUND MARKER XL RAL



Spotmarking aerosols in RAL traffic colours.

- Optimised for ground marking
- Extra large can for more linear metres
- Two finger nozzle for accurate writing
- Quick drying (5 - 10 minutes)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

GROUND MARKER XL RAL

OPIS

For quick and easy marking of construction and excavation sites, underground utilities and for traffic safety. Optimised for ground marking. By means of the 360° valve the aerosol is sprayable in all directions. RUST-OLEUM® Spot Marking Aerosol is based on a fast drying acrylic resin. All products in this range are aromatic free and based on lead- and chromate free pigments.

ZALECANE UŻYCIE

RUST-OLEUM® Marking Aerosol 2800AE can be used on metal, concrete, asphalt, gravel, soil and grass, etc.

RUST-OLEUM® Marking Aerosol 2800AE is not water-soluble and should be used in light industrial exposures, normal humidity and interior applications. RUST-OLEUM® Marking Aerosol 2800AE is designed for quick and easy marking of construction and excavation sites, underground utilities and for traffic safety.

CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk: 20 minutes
Do przemalowania: within 1 hour or after 48 hours
Pełne utwardzenie: 7 days

ZUŻYCIE TEORETYCZNE

750 ml / 2,25 m² per spray can at 25 µm dry (depending on colour)

ZUŻYCIE PRAKTYCZNE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRZYGOTOWANIE POWIERZCHNI

Remove dirt, grease, oil and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

WSKAZÓWKI DOTYCZĄCE UŻYCIA

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

It is not possible to clean the spray button in the usual way. Due to the use of the 360° valve this is not necessary.

WARUNKI APLIKACJI

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO: 637 - 654 g/l
Uwagi dotyczące bezpieczeństwa: Consult Safety Data Sheet and Safety Information printed on the can.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu