

**RUST-OLEUM®**  
INDUSTRIAL



## GRAFFITISHIELD™ HYDRO

# Water-based anti-graffiti coating

- Ideal for natural stone types
- Almost invisible result
- No film building
- Excellent UV-resistance
- Transparent protection

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# GRAFFITISHIELD™ HYDRO

## POPIS PRODUKTU (DLHÝ)

Water based permanent anti-graffiti coating with hydrophobic properties for mineral substrates.

## ODPORÚČANÉ POUŽITIE

GraffitiShield™ HYDRO can be applied to all porous mineral surfaces, such as concrete, brickwork, and dimension stone.

## TECHNICAL DATA

Hustota (g/cm<sup>3</sup>): 1,0  
Úroveň lesku: Matt  
Obsah pevných látok v objeme: 10%

## DRY TIMES BY 20

Na dotyk suché: 1 hour  
Suché na manipuláciu: 1 hour  
Suchý na opätovné natieranie: 1 hour (with itself)  
Úplne vytvrdené: 3 days

## TEORETICKÁ SPOTREBA

5 - 10 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Dependent on many factors, such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

The surface should be clean, dry, and free of dirt and grease.

## NÁVOD NA POUŽITIE

Before use, shake up and stir well to ensure a good degree of homogeneity. Lay on two coats, with a drying interval of at least 60 minutes between coats.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Do not dilute. Nozzle 013-015. It is advisable to cover up windows and doors during application.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Do not dilute. It is advisable to cover up windows and doors during application.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

## POZNÁMKY

Remove graffiti with GraffitiShield™ CLEANER. GraffitiShield™ HYDRO will remain fully intact once graffiti has been removed, allowing for many rounds of cleaning.

## DATA SAFETY DATA

Úroveň VOC: 51 g/l  
VOC readymix: 51 g/l  
Kategória VOC: A/i  
Limit VOC: 140 g/l  
Poznámky k bezpečnosti: Consult the relevant product safety sheet and information on the packaging.

## SKLADOVATELNOSŤ

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu