

**RUST-OLEUM®**  
INDUSTRIAL



## GRAFFITISHIELD™ WAX

# Anti-graffiti coating based on bee wax

- Virtually invisible sacrificial coating for many surface types
- Biodegradable
- Resistant against UV and weathering
- Low solvent content
- Water vapour permeable

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# GRAFFITISHIELD™ WAX

## POPIS PRODUKTU (DLHÝ)

Sacrificial layer based on natural wax. Suitable for a single cleaning process.

## ODPORÚČANÉ POUŽITIE

Once it has hardened, GraffitiShield™ WAX is very resistant to many types of ink and paint. Graffiti can be easily removed with hot water. Once the graffiti has been removed, the cleaned areas should once again be coated with GraffitiShield™ WAX. Once the hardening period has passed, this will ensure that the treated surface is once again resistant to graffiti. Suitable surfaces: dimension stone, brick, calcium silicate, concrete, acrylic, and marble. It is important that the surfaces used can be cleaned under high pressures, at a water temperature of 70-90°C.

## TECHNICAL\_DATA

Hustota (g/cm³): 1,02  
Úroveň lesku: Satin

## DRY\_TIMES\_BY\_20

Na dotyk suché: 1 hour  
Suché na manipuláciu: 12 hours  
Suchý na opätovné natieranie: 2 hours  
Úplne vytvrdnuté: 24 hours

## TEORETICKÁ SPOTREBA

6,7 m²/l

## PRAKTICKÁ VÝDATNOSŤ

Dependent on many factors, such as porosity and roughness of the surface and material losses during application (see DIN 53220).

## PRÍPRAVA POVRCHU

The surface should be clean, dry, and free of dirt and grease.

## NÁVOD NA POUŽITIE

Before use, shake up and stir well to ensure a good degree of homogeneity.

## PODMIENKY APLIKÁCIE

The working temperature range is between 5°C and 35°C.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Warm water.

## POZNÁMKY

Graffiti can be easily removed with a high-pressure cleaner and hot water. When spraying at pressures of 40 bar and upwards, and a minimum temperature of 70-90°C, GraffitiShield™ Wax will melt, removing the graffiti from the surface along with it. After removal, a new layer of GraffitiShield™ Wax should be applied.

## DATA\_SAFETY\_DATA

Úroveň VOC: 25 g/l  
VOC readymix: 25 g/l  
Kategória VOC: A/c  
Limit VOC: 40 g/l  
Poznámky k bezpečnosti: Consult the relevant product safety sheet and information on the packaging.

## SKLADOVATEĽNOSŤ

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu