

RUST-OLEUM®
INDUSTRIAL



GRAFFITISHIELD™ WAX

Anti-graffiti coating based on bee wax

- Virtually invisible sacrificial coating for many surface types
- Biodegradable
- Resistant against UV and weathering
- Low solvent content
- Water vapour permeable

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

GRAFFITISHIELD™ WAX

BESKRIVNING

Sacrificial layer based on natural wax. Suitable for a single cleaning process.

REKOMMENDERAD ANVÄNDNING

Once it has hardened, GraffitiShield™ WAX is very resistant to many types of ink and paint. Graffiti can be easily removed with hot water. Once the graffiti has been removed, the cleaned areas should once again be coated with GraffitiShield™ WAX. Once the hardening period has passed, this will ensure that the treated surface is once again resistant to graffiti. Suitable surfaces: dimension stone, brick, calcium silicate, concrete, acrylic, and marble. It is important that the surfaces used can be cleaned under high pressures, at a water temperature of 70-90°C.

TEKNISK DATA

Densitet: 1,02
Glansnivå: Satin

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr: 1 hour
Hanteringstorr: 12 hours
Övermålningsbar: 2 hours
Fullt härdad: 24 hours

TEORETISK FÖRBRUKNING

6,7 m²/l

PRAKTISK FÖRBRUKNING

Dependent on many factors, such as porosity and roughness of the surface and material losses during application (see DIN 53220).

YTFÖRBEREDELSE

The surface should be clean, dry, and free of dirt and grease.

BRUKSANVISNING

Before use, shake up and stir well to ensure a good degree of homogeneity.

APPLICERINGSFÖRHÅLLANDEN

The working temperature range is between 5°C and 35°C.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

RENGÖRING AV UTRUSTNING/SPILL

Warm water.

ANMÄRKNINGAR

Graffiti can be easily removed with a high-pressure cleaner and hot water. When spraying at pressures of 40 bar and upwards, and a minimum temperature of 70-90°C, GraffitiShield™ Wax will melt, removing the graffiti from the surface along with it. After removal, a new layer of GraffitiShield™ Wax should be applied.

SÄKERHETSDATA

VOC-nivå: 25 g/l
VOC färdigmix: 25 g/l
VOC-kategori: A/c
VOC-gräns: 40 g/l
Anmärkningar om säkerhet: Consult the relevant product safety sheet and information on the packaging.

HÅLLBARHET

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu