

RUST-OLEUM®
INDUSTRIAL



HARD HAT® ADVANCED

The Nr. 1 Industrial Paint Aerosol!

- Ultimate quality Primer & Topcoat in 2 in1
- Strong corrosion protection
- High colour retention
- Flexible - doesn't peel off
- High chemical resistance

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

HARD HAT® ADVANCED

OPIS

Hard Hat Advanced 2700 Primer and Topcoat in 1 sprays are the ultimate industrial lacquer for a wide range of substrates including bare steel or galvanised. Based on a fast drying short oil soya alkyd resin, it's lead, chromate and zinc free, anticipating the most stringent regulations to come. It's proprietary technology confers strong anticorrosive properties, flexibility and excellent chemical resistance to offer longlasting resistance in harsh industrial environments.

ZALECANE UŻYCIĘ

RUST-OLEUM Hard Hat® Advanced 2700 Primer & Topcoat in 1 should be applied over properly prepared painted substrates, bare steel, brushed light rust, galvanised, aluminium and many other substrates. RUST-OLEUM Hard Hat® Advanced 2700 Primer & Topcoats in 1 is intended for small maintenance jobs or for touch-up. RUST-OLEUM Hard Hat® Advanced 2700 Primer & Topcoat in 1 should be used in light industrial exposures, normal humidity for interior & exterior applications.

DANE TECHNICZNE

Stopień połysku: Połysk, Mat, Satyna
Odporność na temperaturę: 100°C (dry heat), above 65°C discoloration may occur

CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk: 20 minutes
Do użytku: 45 minutes
Do przemalowania: Within 1 hour or after 48 hours
Pełne utwardzenie: 7 days

ZALECANA GRUBOŚĆ WARSTWY NA MOKRO

100 µm

ZALECANA GRUBOŚĆ WARSTWY NA SUCHO

25 µm

ZUŻYCIĘ TEORETYCZNE

2.5 -3 m² per spray can at 25 µm dry

ZUŻYCIĘ PRAKTYCZNE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRZYGOTOWANIE POWIERZCHNI

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application.

WARUNKI APLIKACJI

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

APLIKACJA I ROZCIEŃCZANIE: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing balls is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

UWAGI

Bright topcoats may need a light coloured primer/intermediate coat.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO: 640 - 650 g/l
Uwagi dotyczące bezpieczeństwa: Consult Safety Data Sheet and Safety Information printed on the can.

OKRES TRWAŁOŚCI PRODUKTU

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data wydania: 07/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu