

**RUST-OLEUM®**  
INDUSTRIAL



## HARD HAT® TOPCOAT HEAT RESISTANT

# Heat resistant coating up to 750°C



- For continuous temperatures up to 650°C
- For peak temperatures up to 750°C
- For on bare metal or slightly rusted surfaces
- Ideal for engines, heat cannons, pipes, vents, etc.
- To handle after 3 hours (at 20°C)

footer\_main\_page\_line\_one

footer\_main\_page\_line\_two

# HARD HAT® TOPCOAT HEAT RESISTANT

## POPIS PRODUKTU (DLOUHÝ)

Hard Hat® 1015 and 1078 are Heat Resistant Coatings based on a silicone modified alkyd resin.

## DOPORUČENÉ POUŽITÍ

HARD HAT® Heat Resistant Coating can be applied on new, bright or shot-blasted steel or well pre-treated coated surfaces such as barbecues, boiler fittings, hot air cannons, exhausts, etc.

HARD HAT® Heat Resistant Coating is intended for small maintenance jobs and repairs. HARD HAT® Heat Resistant Coating provides protection up to a dry heat of 750°C (short-term peak load) for applications indoors or in a sheltered outdoor environment.

## TECHNICAL DATA

Úroveň lesku:	Matt
Třída koroze:	N / A
Tepelná odolnost:	Standard 600°C (dry heat) / Short term peak 750°C (dry heat)

## DRY TIMES BY 20

Dotykem suché:	2 hours
Suché na manipulaci:	8 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	Allow the product to dry for 3 hours at room temperature and then heat to 150°C in stages of max. 50°C/hour. Allow to cool for 24 hours. The product is now fully cured.

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

85 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35-40 µm

## TEORETICKÁ SPOTŘEBA

10-12 m<sup>2</sup> per litre at 35 - 40 µm dry

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Only apply if the air and surface temperatures are between 5 and 35°C and the relative humidity is less than 85%.

The temperature of the coated surface must be at least 3°C above the dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

No thinning

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

No thinning. Use shorthaired polyamide (perlon 8 - 12 mm) rollers

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Dilute up to 10 to 15% volume RUST-OLEUM Thinner 7301

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

With RUST-OLEUM thinners 7301.

## POZNÁMKY

RUST-OLEUM Heat resistant coating 1015 and 1078 are self-priming and should not be applied on primers or coatings, which are not heat resistant.

## DATA SAFETY DATA

Úroveň těkavých organických látek:	1015: 458 g/l max / 1078: 416 g/l max
VOC ready mix:	1015: 458 g/l max / 1078: 416 g/l max
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu