

RUST-OLEUM®
INDUSTRIAL



HARD HAT® TOPCOAT RAL-COLOURS

The Nr. 1 Industrial Paint Aerosol!

- Top quality
- For on bare metal, wood and concrete
- To handle after 30 minutes (at 20°C)
- Best available hiding power
- Heat-resistant up to 100 °C

footer_main_page_line_one

footer_main_page_line_two

HARD HAT® TOPCOAT RAL-COLOURS

POPIS PRODUKTU (DLHÝ)

Hard Hat® Aerosol Topcoats 2100 are based on a fast drying short oil soya alkyd. The products are based on lead- and chromate free pigments.

ODPORÚČANÉ POUŽITIE

RUST-OLEUM Topcoats 2100 should be applied over RUST-OLEUM Hard Hat 2169/2182 Primers or properly prepared painted substrates. RUST-OLEUM Topcoats 2100 are intended for small maintenance jobs or for touch-up. RUST-OLEUM Topcoats 2100 should be used in light industrial exposures, normal humidity and interior applications.

TECHNICAL_DATA

Úroveň lesku: Gloss, Matt, Satin
Teplotná odolnosť: 100°C (dry heat), above 65°C discoloration may occur

DRY_TIMES_BY_20

Na dotyk suché: 15 minutes
Suché na manipuláciu: 30 minutes
Suchý na opätovné natieranie: Within 1 hour or after 48 hours
Úplne vytvrdené: 7 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

25 µm

TEORETICKÁ SPOTREBA

2.5 m² per spray can at 25 µm dry

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application.

PODMIENKY APLIKÁCIE

For good results the relative humidity shall be below 85% and the temperature of the can above and substrate 0°C.

APLIKÁCIA A RIEDENIE: AEROSÓL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu